

Emission Test Certificate

Thursday, 17th May, 2018

Supplier: Godfrey Hirst Australia (7 Factories Road, Geelong, VIC 3220)

Sample Description: GH 8mm Laminate 1216 x 197 x 8

Date Tested: May 2018 (Tested by FORAY Laboratories – NATA Accreditation 1231)

Test Method: ASTM D5116-2017 “Standard Guide for Small-Scale Environmental Chamber Determinations of Organic Emissions from Indoor Material/Products”.

Emission Data (24 hours):

Global GreenTag	GH 8mm Laminate 1216 x 197 x 8
Total Volatile Organic Compound Emission Rate Limit: <0.500 mg/m ² /hr	Total Volatile Organic Compound Emission Rate: 0.060 mg/m ² /hr
4-phenylcyclohexene Emission Rate Limit: <0.05 mg/m ² /hr	4-phenylcyclohexene Emission Rate: <0.004 mg/m ² /hr
Formaldehyde Emission Rate Limit: <0.1 mg/m ² /hr	Formaldehyde Emission Rate: 0.005 mg/m ² /hr



Dr. Vyt Garnys
 PhD, BSc(Hons) AIMM, ARACI, ISIAQ
 ACA, AIRAH, FMA
 Managing Director and Principal Consultant



Nick Joy
 BSc(Hons)
 Consultant



Tuan Duong
 B.Eng. (Chemical)
 Consultant

CV180476