

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client :	IVC Group Nijverheidsla 8580 Avelger Belgium			Test Nur Issue Da Print Dat	ite	:	17-00644 7/12/2017 31/01/201	7
Sample D	Description	Nominal Mass per Unit Area/De	erogenous PVC floor	-				
S/ISO 9239.′	1-2003	Reaction to Fire Tests for Floo Radiant Heat Source	orings. Determinatio	on of the Burnin	g Beh	avio	our using a	
		Date of Sample Arrival 14/11/2017						
		Date Tested 05/12/2017						
		CHF Value	1	2	3		Mean	
		Length	7.1	-	-		-	kW/m²
		Width	6.7	6.5	6.1		6.4	kW/m²
		Smoke Value	1	2	3		Mean	
		Length	109	-	-		-	%.min
		Width	139	103	149		130	%.min
		The test results relate to the be conditions of the test, they are hazard of the product in use. Sample was conditioned in acc	not intended to be so				•	

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

> Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by

118106

23849

Australian Wool testing Authority Ltd Copyright - All Rights Reserved (C)

0204/11/06



the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Chemical Testing Mechanical Testing Performance & Approvals Testing

: Accreditation No : Accreditation No : Accreditation No

983 985 1356

Page 1 of 1



APPROVED SIGNATORY

Jensue Salations