

# 02GN084 Chrome-Free Epoxy Polyamide Primer

## TECHNICAL DATA SHEET

### Product Description

02GN084 is a chemically cured, chrome-free, two-component epoxy polyamide primer.

- Corrosion inhibiting
- Chemical and solvent resistant
- Resistant to immersion in hydraulic fluids, lubricating oils, phosphate ester based hydraulic fluids and distilled water

### Components



#### **Mix ratio (by volume):**

- 02GN084 (base component) 3 parts
- 02GN084CAT (catalyst component) 1 part

*Note: If additional thinning is required use MIL-T-81772 Type II approved thinner where VOC regulations permit. See Instructions for Use section for more details.*

Available in touch up kits. For more details see [Instructions For Use Section](#).

### Specifications



02GN084 primer is qualified to:

- 5PTMRA01
- MCS 9053
- MIL-PRF-23377 Type I Class N

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

#### **Product Compatibility:**

02GN084 primer is compatible with the following topcoat specifications:

- MIL-PRF-85285
- MMS-420

### Surface Preparation and Pretreatments



02GN084 can be applied over clean, dry, intact aluminum and composite surfaces. Aluminum surfaces shall be treated with materials conforming to MIL-DTL-5541 or equivalent.

# 02GN084 Chrome-Free Epoxy Polyamide Primer

## Instructions for Use



### Mixing Instructions:

Stir or shake the base component to ensure any pigment, which may have settled on the bottom of the can, has been fully incorporated into the base. Do not stir or shake the base component longer than 5 minutes unless sediment is observed. Then shake for another 5 minutes. Slowly add one volume of catalyst to three volumes base component. Mix by hand stirring, paint shaker or mechanical mixing to ensure the base/catalyst mixture is completely homogeneous. Do not shake or mechanically mix material for longer than 10 minutes. Constant agitation of the material during spray application is recommended.

Kit Size	02GN084 Base	02GN084CAT	Yield
GK	96 oz. / 2.84 L	32 oz. / 946 ml	1 gal. / 3.8 L
QK	24 oz. / 710 ml	8 oz. / 234 ml	1 qt. / 946 ml

If additional thinning is required, use IS-237 or other MIL-T-81172 Type II approved thinner. Note that addition of MIL-T-81172 will increase the mixed VOC, therefore consult regional VOC regulations and restrictions.

### 02GN084 is available in 2-ounce and 4-ounce touch up kits:

All touch-up kit configurations consist of an inner cup, which contains the 02GN084CAT catalyst located inside an outer cup (bottle) that contains the 02GN084 base component.

To mix, remove lid, pour contents of inner cup (catalyst) into outer cup (base). Replace lid and shake well by hand, approximately 2 minutes. Material is now ready to apply.

*Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 13° and 35°C (55° to 95°F). The minimum temperature of the paint components should be 13°C (55°F) prior to mixing.*



### Induction Time:

Not Required




### Viscosity (can kits): (23°C/73°F)

- #2 EZ Zahn cup 20 ± 2 seconds
- #4 Ford cup 40 seconds maximum

*Note: Viscosities quoted are the typical values obtained when using specified mix ratio.*

# 02GN084 Chrome-Free Epoxy Polyamide Primer



**Pot Life:**

4 hours @ 21 - 25°C (70 - 77°F)

## Application Guidelines

**Recommended Application Conditions:**

Temperature	15 - 30°C (59 - 86°F)
Relative Humidity	20 - 90%

**Spray application:**

Ground the aircraft and the application equipment before priming. Stir the primer slowly during the application. The suggested film thickness is 15 to 22.5 microns (0.6 to 0.9 mils). This can be accomplished by one medium coat with 50% overlap.

**Touch-Up-Kit application:**

After mixing the touch up kit, use brush or roller to apply.

*These application guidelines represent PPG's best advice in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*




**Theoretical Coverage:**

19 square meters/liter at 25 microns dry film (778 square feet/gallon at 1 mil dry film)  
Recommended dry film thickness; 15 to 22.5 microns (0.6 to 0.9 mils)

**Touch up kit theoretical coverage at 25 microns (1 mil) dry film:**

2 oz. TUK: 12.15 square feet  
4 oz. TUK: 24.3 square feet



**Dry Film Density:**

1.57 grams/cubic centimeter (13.10 pounds/gallon)

**Dry Film Weight:**

3.70 grams/square meter at 25 microns dry film (0.00815 pounds/square feet at 1 mil dry film)

# 02GN084 Chrome-Free Epoxy Polyamide Primer



## Equipment:

02GN084 primer is compatible with all current forms spray equipment.

Equipment Type	Tip Size	Pot Pressure	Atomization Pressure at the Cap
Electrostatic Air Spray Gun	1.2 mm or 1.5 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)
Electrostatic Air Assisted Airless Spray Gun	#611 or #613 (Graco Nomenclature)	700 to 1200 psi (48 to 82 bar)	40 to 60 psi (2.8 to 4.1 bar)
High Volume Low Pressure Spray Gun (HVLP)	1.0 mm to 1.4 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.2 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

## Equipment Cleaning:

Use IS-237 Epoxy Reducer (MIL-T-81772B Type II) to remove any liquid or residual primer from equipment. Once material has cured, use an approved chemical paint removal system to strip primer from parts and equipment

## Physical Properties (product)



**Color:** Light Aqua Green



**Gloss:** Not Applicable



Dry Times	22 - 28°C (71 - 84°F)
Tack Free	5 hours maximum
Topcoat Window	5 - 24 hours
Dry Hard	8 hours maximum
Full Cure	14 days maximum

*Note: Dry times above were established at room (ambient) temperatures, 75° ± 5°F and 50% ± 10% relative humidity at approximately 0.6-1.0 mils of dry film build. After 8 hours cure, solvent wipe the entire primed surface. After 24 hours of cure, scuff sand the entire primed surface followed by solvent wiping prior to top coating. [Ref: T.O. 1-1-8 Section 6.12.2.5, JAN 12, 2010]. Note: Higher temperatures will reduce the recoat time while lower temperatures will increase the recoat times.*

# 02GN084 Chrome-Free Epoxy Polyamide Primer

Forced Dry Schedule: For dry to stack conditions only. Allow a minimum of 15 minutes flash off time at ambient temperatures prior to exposing painted parts to high temperatures. Complete testing should be done prior to use. Below are suggested starting points. Other variables may affect these cure schedules.

Temperature	Time
120°F	45 minutes
140°F	30 minutes
160°F	20 minutes
180°F	15 minutes

*Note: Ambient temperatures are defined as 70° ± 10°F and 50% ± 10% relative humidity.*

## VOC

### VOC:

Mixed, ready to use VOC (EPA method 24)	338 grams/liter
Base Component	405 grams/liter
Catalyst Component	190 grams/liter



### Flash point closed cup:

Base Component	8°C (46°F)
Catalyst Component	8°C (46°F)

### Shelf Life:

**Can kits:** 12 months from date of manufacture

**Touch up kits:** 4 months from date of packaging

*Note: Shelf life is provided for original, unopened containers*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

## Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 21°C to 32°C (70°F to 90°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*

# 02GN084 Chrome-Free Epoxy Polyamide Primer

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200  
Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119  
Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666  
Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

#### **ASC – South Europe**

Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc.  
12780 San Fernando Road  
Sylmar, CA 91342  
[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 11/16  
Lit: 4152