## FORMICA® LAMINATE BY FORMICA GROUP



## BACKING SHEETS TECHNICAL DATA

## PRODUCT DESCRIPTION

Phenolic resin-treated kraft papers are consolidated in a press at high pressures. The sheet back is sanded to maintain a uniform thickness and facilitate bonding.

## RECOMMENDED APPLICATION

#### **GRADE 91/BKL**

Formica® brand backing sheet 91/BKL is intended for interior application to the backside of panels clad with Formica® brand vertical grade postforming decorative laminate to prevent moisture absorption and minimize warpage.

#### **GRADE C2/BKH**

Formica® brand backing sheet C2/BKH is intended for interior application to the backside of panels clad with Formica® brand horizontal grade postforming decorative laminate to prevent moisture absorption and minimize warpage.

#### **GRADE 99/BKH**

Formica® brand backing sheet 99/BKH is intended for interior application to the backside of panels clad with Formica® brand horizontal grade standard decorative laminate to prevent moisture absorption and minimize warpage.

## **FABRICATION AND ASSEMBLY**

#### **LIMITATIONS**

Formica® brand backing sheets are designed for interior use only. Do not adhere directly to plywood, plaster, drywall (gypsum board), or concrete. Do not use in areas exposed to temperatures exceeding 275°F (135°C) or for exterior applications. Backing sheets are not intended for use on the decorative face of any application.

#### **STORAGE**

Backing sheets should be stored horizontally, with the top sheet turned face down and a caul board or other protective sheet placed on top to protect the material from possible damage and reduce the chance of warpage of the top sheets.

Backing sheets should be protected from moisture, and should never be stored in contact with the floor or an outside wall. Optimum conditions for storage are approximately 75°F (24°C), and 45% to 55% relative humidity.

## **PRECONDITIONING**

Prior to fabrication, allow face laminate, backing sheet, and the substrate to acclimate for at least 48 hours at the same ambient conditions. Optimum conditions are approximately 75°F (24°C), and relative humidity of 45% to 55%. Provisions should be made for the circulation of air around the materials.

#### **SUBSTRATES**

Formica® brand backing sheets should be bonded to an appropriate substrate, such as Medium Density Fiberboard (MDF) or a #45 density particleboard (CS 236-66: Type 1, Grade B, Class 2). The substrate should be sanded smooth, and should be clean, free of oil or grease, and uniform in thickness.

#### **ADHESIVES**

Contact, semi-rigid (PVAc), or rigid (urea, resorcinol) adhesives may be used. Follow the adhesive manufacturer's recommendations. Certain combinations of finish, substrate, and adhesive can cause telegraphing. To minimize warpage, use the same adhesive for face and back laminates.

#### **ASSEMBLY**

Material, equipment, and workmanship should conform to the industry standard practices, conditions, procedures, and recommendations as specified by ANSI/NEMA LD3-1995, Section 4, Architectural Woodwork Quality Standards.

Always align sanding marks in the same direction.

Formica® brand backing sheets can be sawed, drilled, routed, and fabricated using standard carbide-tipped cutting tools.

All inside corners of cutouts must be radiused as large as possible,  $\frac{1}{8}$ " (3.18mm) minimum, to avoid stress cracking. The edges and corners should be routed, sanded, or filed smooth and free of chips or nicks.

## **TECHNICAL DATA**

Performance compliance of Formica® brand Backing Sheets:

#### ANSI/NEMA STANDARDS PUBLICATION - LD3-2005

		FORMICA® BRAND BACKING SHEET			
PHYSICAL PROPERTIES	LD3 TEST	GRADE 99/BKH	GRADE C2/BKH	GRADE 91/BKL	
Thickness - in - mm	n/a	0.039" 1.0mm	0.031" 0.8mm	0.024" 0.5mm	

## **CODES AND SPECIFICATIONS**

# FORMICA® BRAND BACKING SHEET, GRADE 91/BKL

- U.S. Federal Specification, LP508-H, Style ND, Type IV
- International Organization of Standardization, ISO 4586-2

# FORMICA® BRAND BACKING SHEET, GRADE C2,99/BKH

- U.S. Federal Specification, LP508-H, Style ND, Type IV
- International Organization of Standardization, ISO 4586-2

## FIRE TEST DATA - ASTM E-84

Fire test data for selected panel assemblies using Formica brand decorative face laminate incorporating Formica® brand backing sheets are listed in the *Postforming and General Purpose Laminate Technical Data* sheets. Test reports are available upon request.



## BACKING SHEETS TECHNICAL DATA

## SIZES AND FINISHES

#### **GRADE 91/BKL**

## Natural Finish (-00)

Dull, utility finish inherent with materials and press method. Natural finish is not intended for use on the decorative face of any application.

#### Sizes

Width: 48" (121.9cm), 60" (152.4cm) Length: 96" (243.8cm), 120" (304.8cm), 144" (365.8cm)

## GRADE C2, 99/BKH\*

## Natural Finish (-00)

Dull, utility finish inherent with materials and press method. Natural finish is not intended for use on the decorative face of any application.

#### Sizes:

Width: 48" (121.9cm), 60" (152.4cm) Length: 96" (243.8cm), 120" (304.8cm), 144" (365.8cm) 'Available on a factory order basis

## **COLORS**

Dark brown, inherent with materials and press methods.

Samples are available from Formica Corporation specification representatives or directly from Formica Corporation. Call 1-800-FORMICA $^{\text{\tiny{M}}}$ .

## **HOW TO SPECIFY**

Backers shall be Formica® brand backing sheets produced by Formica Corporation, Cincinnati, Ohio.

G	R	Α	D	Е
٠.			_	_

FINISH NATURAL (00)

## SIZE

All backing sheets shall meet the minimum performance standards of the International Organization of Standardization, ISO 4586-2, and National Electrical Manufacturers Association, ANSI/NEMA LD3-1995. Note to specifier: For U.S. Government projects, refer to Federal Specification LP508-H, Style ND, Type IV.

## **USE AND CARE**

Formica® brand backer sheets are a utility grade and not intended for use where maintenance is required. They may be wiped clean with a clean, non-abrasive, damp cloth and mild liquid detergent or household cleaner. More stubborn dirt, grease or adhesive spills may be removed with lacquer thinner or contact adhesive solvents.

# FORMICA® LAMINATE BY FORMICA GROUP



## BACKING SHEETS TECHNICAL DATA

#### LIMITED WARRANTY

Formica Corporation expressly warrants that, for a period of one (1) year from the date of first sale, these products will be reasonably free of defects in materials and workmanship, and that when properly handled and fabricated, will conform, within accepted tolerance, to applicable manufacturing specifications. Colors subject to dye lot variations. This limited warranty only applies to Formica® Brand Laminate which is stored, handled, fabricated and installed in the manner recommended by Formica Corporation. Due to the variety of uses and applications to which Formica® Brand Laminate may be put, FORMICA CORPORATION CAN MAKE NO WARRANTY THAT THIS PRODUCT IS SUITABLE FOR ANY PARTICULAR PURPOSE AND CAN MAKE NO OTHER WARRANTIES, EXPRESS OR IMPLIED, OTHER THAN THOSE SET FORTH ABOVE.

## **DISCLAIMER OF WARRANTIES**

THE WARRANTIES SET FORTH HEREIN OR IN FORMICA CORPORATION'S WARRANTY DOCUMENTS WITH RESPECT TO A PRODUCT ARE THE ONLY WARRANTIES MADE BY FORMICA CORPORATION IN CONNECTION WITH THESE PRODUCTS, AND ARE EXPRESSLY IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. PRODUCTS SOLD BY FORMICA CORPORATION ARE SOLD ONLY TO THE SPECIFICATIONS SPECIFICALLY SET FORTH BY FORMICA CORPORATION IN WRITING. FORMICA CORPORATION'S SOLE OBLIGATION FOR A REMEDY TO BUYER SHALL BE REPAIR OR REPLACEMENT OF NON-CONFORMING PRODUCTS, OR AT THE OPTION OF FORMICA CORPORATION, RETURN OF THE PRODUCT AND REFUND OF THE PURCHASE PRICE. BUYER ASSUMES ALL RISK WHATSOEVER AS TO THE RESULT OF THE USE OF THE PRODUCTS PURCHASED, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

## LIMITATION OF LIABILITY

No claim by buyer of any kind, including claims for indemnification, whether as to quality or amount of products delivered or for nondelivery of products, shall be greater in amount than the purchase price of the products in respect of which damages are claimed. IN NO EVENT SHALL FORMICA CORPORATION BE LIABLE TO BUYER FOR ANY SPECIAL, INDIRECT, INCIDENTAL, RELIANCE, EXEMPLARY, OR CONSEQUENTIAL DAMAGES OR COVER, OR LOSS OF PROFIT, REVENUE OR USE, IN CONNECTION WITH, ARISING OUT OF, OR AS A RESULT OF, THE SALE, DELIVERY, SERVICING, USE OR LOSS OF USE OF THE PRODUCTS SOLD HEREUNDER, OR FOR ANY LIABILITY OF BUYER TO ANY THIRD PARTY WITH RESPECT THERETO. BUYER SHALL INSPECT FOR NONCONFORMITY PROMPTLY UPON RECEIPT. Failure by buyer to give Formica Corporation written notice of claim within 30 days from date of delivery or, in the case of non-delivery from the date fixed for delivery, shall constitute a waiver by buyer of all claims in respect of such products.

This limited warranty gives purchaser of Formica® Brand Laminate specific legal rights. Other rights may be available and vary from state to state.

Any information or suggestion concerning application, specifications or compliances with codes and standards is provided solely for your convenient reference and without any representation as to accuracy or suitability. Formica Corporation disclaims any legal responsibility. The user must verify and test the suitability of any information or products for their own particular purpose of specific application.

## **MANUFACTURER**

Formica® Brand Laminate sheets are manufactured by Formica Corporation.

#### **TECHNICAL SERVICES**

Technical assistance may be obtained through your local Formica® Brand Products Distributor or from Formica Corporation trained representatives in sales offices throughout the country. To assist these representatives, Formica Corporation maintains a sales and technical services staff in Cincinnati, Ohio. For technical assistance, contact your distributor or sales representative; write the company directly at Formica Corporation Technical Services Department, 10155 Reading Road, Cincinnati, OH, 45241; call (513) 786-3578 or 1-800-FORMICA™; or fax (513) 786-3195. In Canada, call 1-800-363-1405. In Mexico, call (525) 530-3135.

Formica is a sublicensed trademark to Formica Corporation. Formica and the Formica Anvil logo are registered trademarks of The Diller Corporation. 1-800 -FORMICA is a trademark of The Diller Corporation. The products and manufacturing processes of Formica Corporation are protected under U.S. and foreign patents.

All  $^{\odot}$  brands are registered trademarks of the respective owners. All  $^{\rm m}$  brands are trademarks of the respective owners.

For warranty information, please visit www.formica.com or call 1-800 -FORMICA™.

©2019 Formica Corporation Cincinnati, Ohio 45241