

ANTICORIT DFW 8301

Dewatering / Corrosion Preventive Oil

Description

ANTICORIT DFW 8301 is our newest generation barium free corrosion preventive and dewatering fluid that produces a thin, waxy film. The new formulation considerably improves the performance of the product, providing for example better demulsifying and corrosion protective properties. Because of the carefully chosen additives, ANTICORIT DFW 8301 is almost odourless.

ANTICORIT DFW 8301 is used for the corrosion protection of metal parts, tools, machine components, gears, motors and spare parts. The thin, waxy film is compatible with all conventional motor and gear oils and does not have to be removed before installation or start up. ANTICORIT DFW 8301 is stable against acidic or alkaline contamination and is therefore especially suitable for use in the galvanising industry for conservation and drying.

ANTICORIT DFW 8301 is suitable for inter-process, storage, and also as transport protection of components. It may be combined with VCI-products. We recommend the application of ANTICORIT VCI products.

By the implementation of a fluorescent dye, an optical detection of the product on the metal surface is possible.

Application

ANTICORIT DFW 8301 is typically used in dipping-baths. It can also be sprayed. The valid safety regulations have to be taken into account.

ANTICORIT DFW 8301 can be removed with water based industrial cleaners or with solvents of the RENOCLEAN series. In some applications a removal from the surface is not necessary as ANTICORIT DFW 8301 is compatible with common lubricants.

Advantages

- Odourless
- Intensive and improved dewatering
- Very Good corrosion protection
- Thin, waxy-greasy film
- All-round applicable
- Free of barium
- Very good compatibility with many materials

Storage conditions

If sealed in the original container the product can be stored at temperatures between + 5 °C to + 40 °C for 3 years.

The indication of a minimum period of storage does not include any guarantee of durability.

ANTICORIT DFW 8301

Dewatering / Corrosion Preventive Oil

Typical chemical and physical properties:

| Property | Unit | Value | Test method |
|---|-------------------|-------|--------------------------|
| Color | | 3,5 | DIN ISO 2049 |
| Flashpoint | °C | >70 | DIN EN ISO 2719 |
| Density at 15 °C | kg/m ³ | 800 | DIN 51 757 |
| Film weight | g/m ² | 2,5 | FLV-F-03 *) |
| Evaporation residue | % | 24 | FLV-V-01 *) |
| Water displacement in 3 min | % | 90 | FLV-W-03 *) |
| <i>Corrosion Protection Data (St 1405) at 2.5 g/m²</i> | | | |
| Salt spray test | hours | > 50 | DIN EN ISO 9227 |
| Condensation climate | cycles | > 50 | DIN EN ISO 6270-2 AHT |
| Copper strip test (3h / 100°C / 0,01% sulphur) | | 1 | DIN EN ISO 2160 |

The above data is typical of normal production and should not be taken as a specification.

*) FLV = Test procedure of FUCHS SCHMIERSTOFFE GMBH