

Lubricant Analysis Report

North America: +1-877-808-3750

Latin America: +1-317-808-3750 / +502-3093-6466 (WhatsApp)

Europe: +1-317-808-3750

Overall report severity based on comments.

Account Information	Component Information	Sample Information							
Account Number: 153995-0003-0000	Component ID: 2011JDFF135DX E	Tracking Number: 23209G30305							
Company Name: BOOM & BUCKET	Secondary ID: A6419627	Lab Number: H-488400							
Contact: STEVEN MESA	Component Type: UNIDENTIFIED ENGINE	Lab Location: Houston							
Address: 701 BRAZOS ST. STE 300	Manufacturer: Information Requested	Data Analyst: AC							
AUSTIN, TX US	Model: Information Requested	Sampled: 27-Sep-2023							
Phone Number: 888-417-3477	Application: UNKNOWN	Received: <mark>05-Oct-2023</mark>							
	Sump Capacity:	Completed: 06-Oct-2023							
Filter Information	Miscellaneous Information	Product Information							
Filter Type: Information Requested		Product Manufacturer: Information Requested							
Micron Rating: 0		Product Name: Information Requested							
		Viscosity Grade: Information Requested							
Comments TITANILIM may be an additive in this Jubricant: In order to properly compare data to the correct standards, please provide COMPONENT									

TITANIUM may be an additive in this lubricant; In order to properly compare data to the correct standards, please provide COMPONENT MANUFACTURER and MODEL, and the FLUID MANUFACTURER, PRODUCT NAME, and VISCOSITY GRADE. Unit and/or lubricant TIME

	Wear Metals (ppm)										Contaminant Metals (ppm) Multi-Source Metals (ppm)					Additive Metals (ppm)								
Sample #	Iron	Chromium	Nickel	Aluminum	Copper	Lead	Tin	Cadmium	Silver	Vanadium	Silicon	Sodium	Potassium	Titanium	Molybdenum	Antimony	Manganese	Lithium	Boron	Magnesium	Calcium	Barium	Phosphorus	Zinc
1	3	0	0	1	1	1	0	0	0	0	6	4	2	87	4	0	0	0	159	430	1732	0	1023	1160

		Sample	e Inforr	nation				Contaminants					luid Pr	operties	5	
Sample #	ate Saı	Date Received	ح Lube Time	ح Unit Time	Lube Change	Eube Added	Filter Change	% Fuel Dilution	% %	% Water	Viscosity ب 40°C	Viscosity بې 100°C	HOX Acid	S Base No.	g sq Oxidation	y sda Nitration / wm1.0
1	27-Sep-2023	05-Oct-2023	0	0	Unk	0	Unk	<2 - Estimate	<.1	<.1 - FTIR		14.5		7.22	10	6

				Partio	le Count	Additional Testing					
Sample #	opo Cog OSI Based On 4/6/14	mL ^ particles /	9 ^ particles / mL	OL A particles / mL	barticles /	72 ^ particles / mL	&	OZ ^ particles / mL	00 ^ particles / mL	Test Method	
1	11										

Comments are advisory only and are based on the assumption that the sample and data submitted are valid. Results relate only to the items tested. Missing fluid or component information limits the $evaluation. \ No\ warranty\ is\ expressed\ or\ implied.\ Measurement\ uncertainty\ available\ upon\ request.$