

Lubricant Analysis Report

North America: +1-877-808-3750

Latin America: +1-317-808-3750 / +502-3093-6466 (WhatsApp) Europe: +1-317-808-3750

Overall report severity based on comments.

Account Information	Component Information	Sample Information
Account Number: 153995-0000-0000	Component ID: 2013 CATERPILLAR 279C E	Tracking Number: 23209G30303
Company Name: BOOM AND BUCKET	Secondary ID: B&B A4730747	Lab Number: H-488915
Contact: ADAM LAWRENCE/KRIS HUFF	Component Type: DIESEL ENGINE	Lab Location: Houston
Address: C/O SAMIR SHAH 71 PARK	Manufacturer: Information Requested	Data Analyst: FLG
DRIVE	Model: Information Requested	Sampled: 04-Oct-2023
ATHERTON, CA 94027 US	Application: UNKNOWN	Received: 05-Oct-2023
Phone Number: 213-463-5980/775-225-3529	Sump Capacity:	Completed: 06-Oct-2023
511. x 6	N. II 7.6	
Filter Information	Miscellaneous Information	Product Information
Filter Type: Information Requested		Product Manufacturer: Information Requested
Micron Rating: 0		Product Name: Information Requested
		Viscosity Grade: Information Requested
Comments Data indicates no abnormal finding	ns. Resample at normal interval. In order to properly	v compare data to the correct standards inlease

	provide COMPONENT MANUFACTURER and MODEL, and the FLUID MANUFACTURER, PRODUCT NAME, and VISCOSITY GRADE. Unit and/or lubricant TIME missing.															t							
	Wear Metals (ppm)									ntamin tals (p		N	Ոսlti-Տ	ource	Metal	ls (ppn	า)	Д	dditive	e Meta	ls (ppr	n)	
Г																	T	Ī .					

												ntamin	ant											
	Wear Metals (ppm)										Metals (ppm)			Multi-Source Metals (ppm)					Additive Metals (ppm)					
Sample #	Iron	Chromium	Nickel	Aluminum	Copper	Lead	Tin	Cadmium	Silver	Vanadium	Silicon	Sodium	Potassium	Titanium	Molybdenum	Antimony	Manganese	Lithium	Boron	Magnesium	Calcium	Barium	Phosphorus	Zinc
1	34	1	0	3	3	0	1	0	0	0	7	4	2	0	55	0	0	0	80	476	2311	0	1101	1300

		Sample	e Inforr	mation					Contaminants	Fluid Properties							
pole #	e Sampled	e Received	Lube Time	Unit Time	e Change	Lube Added	ır Change	Fuel Dilution	Soot	Water	Viscosity 40°C	Viscosity 100°C	Acid Number	Base No. D4739	Oxidation	Nitration	
San	Date	Date	h	h	Lub	gal	Filte	%	%	%	cSt	cSt	mg KOH / g	mg KOH / g	abs / cm	abs / 0.1mm	
1	04-Oct-2023	05-Oct-2023	0	0	Unk	0	Unk	<2 - Estimate	0.4 - E2412	<.1 - FTIR		16.2		5.91	16	11	

_	-				-				-				1						
				Partio	le Count	(particle	s/mL)				Additional Testing								
Sample #	Based On	mL ^ particles /	ں ۸ particles / mL	0 / particles / mL	mL ^ terricles /	/ / particles / mL	& & & & & & & & & & & & & & & & & & &	02 ^ /particles / mL	^ particles / mL	Test Method									
	. / /																		

Comments are advisory only and are based on the assumption that the sample and data submitted are valid. Results relate only to the items tested. Missing fluid or component information limits the evaluation. No warranty is expressed or implied. Measurement uncertainty available upon request.