



# Lubricant Analysis Report

North America: +1-877-808-3750  
 Latin America: +1-317-808-3750 / +502-3093-6466 (WhatsApp)  
 Europe: +1-317-808-3750

0	1	2	3	4
NORMAL		ABNORMAL	CRITICAL	

Overall report severity based on comments.

Account Information		Component Information		Sample Information	
Account Number: 153995-0002-0000 Company Name: BOOM & BUCKET Contact: KRIS HUFF Address: 600 CONGRESS AVE AUSTIN, TX US Phone Number: 1888-313-1597/909-846-6495		Component ID: HHKHFA03LG0000188 MAIN E Secondary ID: Hyundai Component Type: DIESEL ENGINE Manufacturer: <a href="#">Information Requested</a> Model: <a href="#">Information Requested</a> Application: FORKLIFT Sump Capacity:		Tracking Number: 23265Y85686 Lab Number: S-119331 Lab Location: Salt Lake City Data Analyst: ZXH Sampled: 15-Feb-2024 Submitted: 15-Feb-2024 Received: 20-Feb-2024 Completed: 21-Feb-2024	
Filter Information		Miscellaneous Information		Product Information	
Filter Type: <a href="#">Information Requested</a> Micron Rating: 0				Product Manufacturer: <a href="#">Information Requested</a> Product Name: <a href="#">Information Requested</a> Viscosity Grade: <a href="#">Information Requested</a>	
Comments		Flagged data does not indicate an immediate need for maintenance action. Continue to observe the trend and monitor equipment and fluid conditions. Aluminum is at a MINOR LEVEL; ALUMINUM sources in ENGINES include pistons, block and components (intake manifold, head, bearing caps), thrust bearings, main/rod bearing overlay or backing, alumina silica, or contamination from grease. In order to properly compare data to the correct standards, please provide COMPONENT MANUFACTURER and MODEL, and the FLUID MANUFACTURER, PRODUCT NAME, and VISCOSITY GRADE. Unit and/or lubricant TIME missing.			

Sample #	Wear Metals (ppm)										Contaminant Metals (ppm)			Multi-Source Metals (ppm)					Additive Metals (ppm)					
	Iron	Chromium	Nickel	Aluminum	Copper	Lead	Tin	Cadmium	Silver	Vanadium	Silicon	Sodium	Potassium	Titanium	Molybdenum	Antimony	Manganese	Lithium	Boron	Magnesium	Calcium	Barium	Phosphorus	Zinc
1	51	1	0	26	13	1	1	0	0	0	5	12	2	0	65	0	1	0	2	1080	1145	0	1162	1269

Sample Information									Contaminants			Fluid Properties				
Sample #	Date Sampled	Date Received	Lube Time	Unit Time	Lube Change	Lube Added	Filter Change	Fuel Dilution	Soot	Water	Viscosity 40°C	Viscosity 100 °C	Acid Number	Base No. D4739	Oxidation	Nitration
			h	h		qt		%	%	%	cSt	cSt	mg KOH / g	mg KOH / g	abs / cm	abs / 0.1mm
1	15-Feb-2024	20-Feb-2024	0	0	No	0	No	<2 - Estimate	<.1	<.1 - FTIR		14.8		7.82	9	4

Particle Count (particles/mL)										Additional Testing		
Sample #	ISO Code	> 4	> 6	> 10	> 14	> 21	> 38	> 70	> 100	Test Method		
	Based On 4/6/14	particles / mL	particles / mL	particles / mL	particles / mL	particles / mL	particles / mL	particles / mL	particles / mL			
1	/ /											

Comments are advisory only and are based on the assumption that the sample and data submitted are valid. Results relate only to the items tested. Missing fluid or component information limits the evaluation. No warranty is expressed or implied. Measurement uncertainty available upon request.