



# Confidential Report

**Our Ref: 25/12343B3/05/24**





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 June 2024

Our Ref: 25/12343B3/05/24  
Your Ref: ---

Page: 1 of 9

Client:

**Jacaranda Carpets Limited**

1 Cockerel Rise  
Magnetic Park  
Desborough  
Northamptonshire  
NN14 2WE

Job Title:

Fire Classification of One Sample of Carpet

Clients Order Ref:

-

Date of Receipt:

15 May 2024

Description of Sample:

One sample of cut pile, textile backed, handwoven carpet, referenced Kochi (25% Wool and 75% Cashmere).

Work Requested:

We were asked to make the following test(s):

BS EN 13501-1

- \* subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited

Note: This report relates only to the items tested.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.



1066

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)

Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 June 2024

Our Ref: 25/12343B3/05/24

Your Ref: ---

Page: 2 of 9

Client:

Jacaranda Carpets Limited

## Product Description Sheet

(as supplied by the client)

Name and/or Identification of the Product Tested	<b>Kochi</b>
Construction of Carpet (tufted, Wilton etc)	<b>100% Wool (Cashmere)</b>
Pile Fibre Composition (%)	<b>Action Back</b>
Backing Type (if applicable)	<b>PP</b>
Backing Components	<b>5300 g/m<sup>2</sup></b>
Total Carpet Mass per Unit Area (g/m <sup>2</sup> )	<b>4300 g/m<sup>2</sup></b>
Total Pile Mass per Unit Area (g/m <sup>2</sup> )	<b>20mm</b>
Total Thickness (mm)	<b>17mm</b>
Pile Thickness (mm)	<b>18 Tufts</b>
Pitch/Stitch (tufts per 10cm)	<b>20 Tufts</b>
Rows/Gauge (tufts per 10cm)	<b>N.A.</b>
Quantity and Number of Flame-Retardant Coating	<b>Nil</b>



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL. A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)

Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 June 2024

Our Ref: 25/12343B3/05/24

Your Ref: ---

Page: 3 of 9

Client: Jacaranda Carpets Limited

## **FIRE TESTS ACCORDING TO BS EN ISO 11925-2:2020**

### **Reaction to fire tests for building products – Part 2: Ignitability when subjected to direct impingement of flame**

Date of Test: 07/06/24

### **Conditioning**

Test specimens and filter paper conditioned as described in BS EN 13238:2010.

### **Procedure**

The sample was tested in accordance with BS EN ISO 11925-2:2020.

Three specimens from each direction were tested in accordance with the above standard. Specified filter paper was placed beneath the specimen holder and replaced between tests.

The specimens were mounted vertically in the specimen holder so that one end and both sides were enclosed with the exposed end 30mm from the end of the frame. The burner was inclined at an angle of 45°. The flame height was set at 20 mm with the flame impinging on the specimen for 15 seconds on the centre line, 40 mm above the bottom edge.

A marker was placed 150 mm above the upper end of the burner and the time recorded when the flame tip reached the marker, if applicable. The following parameters were also recorded:-

1. If ignition occurs
2. Presence of flaming debris, if applicable
3. Ignition of the filter paper, if applicable

### **Duration of test**

For a flame application time of 15 seconds, the total test duration is 20 seconds after application of the flame.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)

Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 June 2024

Our Ref: 25/12343B3/05/24

Your Ref: ---

Page: 4 of 9

Client: **Jacaranda Carpets Limited**

## Classification Criteria

The samples were classified according to BS EN 13501-1:2018 Fire classification of Construction Products and Building Elements: Part 1 – Classification using Test Data from Reaction to Fire Tests, Table 1 – Classes of reaction to fire performance for construction products excluding floorings.

Flaming Classification	
Classification	Criteria (mean values)
$E_{FL}$	$F_s \leq 150\text{mm}$ within 20 seconds
$F_{FL}$	Fails Class $E_{FL}$

Flaming droplets / particles classification	
Classification	Criteria
No classification	Pass
d2	Fail (Ignition of paper)

## Results

Specimen	Ignition (Yes or No)	Tip of flame reaches 150mm		Flaming droplets	
		Yes or No	Time taken (s)	Yes or No	Ignition of Filter paper (Yes or No)
Machine Direction	1	Yes	No	N/A	No
	2	Yes	No	N/A	No
	3	Yes	No	N/A	No
Across Machine Direction	1	Yes	No	N/A	No
	2	Yes	No	N/A	No
	3	Yes	No	N/A	No

## Note

The specimens of floor covering were tested loose laid over a 6mm fibre cement board, as defined in BS EN 13238:2010.

The substrate used was a fibre cement board (ISO 390) with a thickness of (6±1)mm and a density of (1,800±200) Kg/m<sup>3</sup> representing the standard substrate of Class A1fl or A2fl.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)

Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 June 2024

Our Ref: 25/12343B3/05/24

Your Ref: ---

Page: 5 of 9

Client: Jacaranda Carpets Limited

## FIRE TESTS ACCORDING TO BS EN ISO 9239-1:2010

### Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2010)

Date of Test: 07/06/24

## Conditioning

The specimens were conditioned in accordance with BS EN 13238:2010. The substrate used was a fibre cement board (ISO 390) with a thickness of (6±1)mm and a density of (1,800±200) Kg/m<sup>3</sup> representing the standard substrate of Class A1fl or A2fl.

## Procedure

The test was carried out in accordance with BS EN ISO 9239-1:2010. The sponsor sampled and cut the specimens to the dimensions stated.

Specimens were individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11.0 kW/m<sup>2</sup> to 1.0 kW/m<sup>2</sup> along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, whichever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)

Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 June 2024

Our Ref: 25/12343B3/05/24

Your Ref: ---

Page: 6 of 9

Client: **Jacaranda Carpets Limited**

## Classification Criteria

The samples were classified according to BS EN 13501-1:2018 - Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For floorings, including their surface coverings the classes are:

Classification	Classification Criteria (mean values) (kW/m <sup>2</sup> )
Bfl	8.0
Cfl	4.5
Dfl	3.0
Smoke Production % x min	
s1	≤ 750
s2	Not s1

When tested to BS EN ISO 11925-2:2020 the sample has to have a flame spread (Fs) of: Fs ≤ 150mm within 20 seconds (Class Efl).

## Results

The test results relate to the behaviour of the test specimens of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)

Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 June 2024

Our Ref: 25/12343B3/05/24

Your Ref: ---

Page: 7 of 9

Client: Jacaranda Carpets Limited

## Results (Continued)

Specimen No.	Direction of specimen	Smoke Obscuration Max %	Smoke Obscuration % x min	Maximum Flame front (mm)	Critical Heat Flux (kW/m <sup>2</sup> )	Duration of Flaming (sec)
1	Machine	35	61	450	4.6	729
2	Across	32	66	380	5.6	738
3	Machine	34	65	355	6.0	736
4	Machine	33	71	360	6.0	729
Mean of 4 specimens	Machine	34	66	388	5.5	731

Distance Burnt (mm)	Time for each specimen to burn (s)			
	1	2	3	4
50	127	124	125	125
100	132	129	130	130
150	142	136	139	140
200	150	146	149	149
250	164	161	160	167
300	187	190	192	211
350	222	286	228	300
400	249	-	-	-
450	286	-	-	-

## Note

One specimen was initially tested in each direction and whichever direction gave the worst result a further two specimens were tested. Only the results of the 3 specimens in the same direction were used to calculate the mean results.

The specimens of floor covering were tested loose laid over a 6mm fibre cement board, as defined in BS EN 13238:2010.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 June 2024

Our Ref: 25/12343B3/05/24  
Your Ref: ---

Page: 8 of 9

Client: **Jacaranda Carpets Limited**


## Comment

The results meet the requirements of a **Class Cfl-s1**, as specified in BS EN 13501-1:2018.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<https://www.bttg.co.uk/about-us/decision-rules-policy/>) for further information.

Reported by:  B Marsden (Mrs), Senior Laboratory Technician

Countersigned by:  P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 June 2024

Our Ref: 25/12343B3/05/24  
Your Ref: ---

Page: 9 of 9

Client: Jacaranda Carpets Limited

## Uncertainty Budget

The uncertainty budget for BS EN 13501-1:2018 was determined as follows:-

### BS EN ISO 11925-2:2020

±2 seconds for time recorded removal of flame and terminate test

### Overall (BS EN ISO 9239-1:2010)

The uncertainty varies, therefore:

- a) At position between 0 – 450mm ±7%
- b) At position between 450mm -1000mm ±8%

Smoke Obscuration - ±15%



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.