



Sikabond AT

Universal adhesive system

Application

- Multi purpose adhesive for internal and external bonding requirements
- Can be used as a high modulus sealant

Key Features

- Very good adhesion without priming on many substrates including:
- Hard PVC, GRP, wood, ceramic, tile, brick, concrete, aluminium, stainless steel etc.
- Good initial tack and fast curing with good weathering and water resistance
- Solvent and silicone free, non corrosive
- Compensation for substrate unevenness

Sikabond AT universal adhesive system

Code	Size	Colour
SB-AT-UNIVERSAL	300ml	Dark grey



SB-AT-UNIVERSAL

Technical information	
Skinning time	35 minutes (+23°C/50% r.h.)
Curing rate	~3mm/24H (+23°C/50% r.h.)
Sag flow	0mm, very good (DIN EN ISO 7390)
Service temperature	-40°C to +80°C
Application temperature	+5°C to +40°C
Shear strength	~1.0 N/mm ² ; 1mm adhesive thickness (+23°C/50% r.h.) (DIN 52 283)
Tensile strength	~1.5 N/mm ² ; (+23°C/50% r.h.) (DIN 53 504)
Tear strength	~5 N/mm ² ; (+23°C/50% r.h.) (DIN 53 515)
Elongation at break	~400% (+23°C/50% r.h.) (DIN 53 504)
Elastic recover	>70% (+23°C/50% r.h.) (DIN EN ISO 7389 B)

FIXFAST Ltd | Merlin House | Seven Mile Lane | Borough Green | Sevenoaks | Kent | TN15 8QY
T: 0845 450 4783 | F: 0845 450 7486 | E: info@fixfast.com | W: www.fixfast.com

*Fixfast is a trading name of FIXFAST Ltd which is a company registered in England & Wales with number 09481218.
 The registered office is Fixfast, Merlin House, Seven Mile Lane, Borough Green, Sevenoaks, Kent, United Kingdom TN15 8QY*

© Fixfast July 2017. Due to a policy of continual development, Fixfast reserves the right to change product specification and descriptions without prior notice.



Certificate Number 10905
 ISO 9001: 2008
 ISO 14001: 2004
 BS OHSAS 18001: 2007