

Technical Datasheet

Variostep Classic

Direct Pressure Laminate, Level of use according to EN 13329: class **23/32 – AC4**



Heavy domestic use



Commercial general use



20 years

guarantee

The guarantee applies to the living area according to warranty regulations*



DIMENSION

dimension	thickness (d)	8 ± 0,50 mm · dmax - dmin ≤ 0,50 mm		
	length	1285 ± 0,50 mm		
	width (b)	192 ± 0,10 mm · bmax - bmin ≤ 0,20 mm		
profile	long side	twin clic	short side	1 clic2go
groove	long side		short side	



EN 14041:2004/AC:2006; Cfl-s1; E1; DS; PCP < 5ppm, Bodenbeläge für die Verwendung in Gebäuden. For internal use as floor coverings (see EN 14041), DOP: LW0012016/NB 0766; NB 0767; Kronoflooring GmbH, Mühlbacher Str.1, 01561 Lampertswalde, Germany, www.krono-original.com/en/guarantee

TOLERANCE

squareness	EN 13329	≤ 0,20 mm
straightness	EN 13329	≤ 0,30 mm
flatness crosswise	EN 13329	concave: ≤ 0,15% · convex: ≤ 0,20%
flatness length	EN 13329	concave: ≤ 0,50% · convex: ≤ 1,00%
gaps between elements	EN 13329	average: ≤ 0,15 mm · max: ≤ 0,20 mm
height difference between elements	EN 13329	average: ≤ 0,10 mm · max: ≤ 0,15 mm
misalignment		± 2 mm

TEST

abrasion resistance	EN 13329	AC4 (≥ 4000 rpm)
impact resistance	EN 13329	small ball ≥ 12 N · big ball ≥ 750 mm
stain resistance	group 1 & 2	grade 5
	group 3	≥ grade 4
castor chair test	EN 13329	no change in appearance or damage, as defined per EN 425
effect of a furniture leg	EN 13329	no damage shall be visible, when tested with foot type 0
thickness swelling	EN 13329	≤ 18%
static indentation	EN 13329	≤ 0,05 mm
light fastness	EN 13329	grey scale ≥ 4 at blue wool grade 6
dimensional variations after changes in relative humidity	EN 13329	lengthwise ≤ 0,9 mm · crosswise ≤ 0,9 mm
locking strength	EN 13329	length ≥ 1 kN/m · width ≥ 2 kN/m
surface soundness	EN 13329	≥ 1,25 N/mm ²

ENVIRONMENT

emission of formaldehyde	EN 717-1	Klasse E1
--------------------------	----------	-----------

PHYSICAL BEHAVIOR

fire behavior	EN 13501-1	Cfl s1
slide resistance	EN 13893	technical class DS
thermal resistance	EN 12667	0,073 (m ² K)/W ± 15%
thermal conductivity	EN 12664	0,110 W/(m*K) ± 15%

*Detailed warranty conditions are available at www.krono-original.com

For further information, please see: www.blauer-engel.de