

## Mocha Oak Herringbone

27SPC-HER-MO

1.8m<sup>2</sup>/box 48 box/pallet

100 x 600 x (4/0.5mm)(1mm Underlay built in)



### Product

Click LVT Rigid Core SPC

EN ISO 10582

SPC Flooring

Installation

Unilin Angle




Application

EN ISO 10874

23/33



### Specification

Thickness		EN ISO 24337	4.0mm & 1mm underlay built on
Weight		EN ISO 24342	2.08kg/m <sup>3</sup>
Wear Layer		EN ISO 24346	0.5mm

### Product Properties

Property	Test Method	Result
Indoor air certificate		Floor-score
Fire resistance	EN 13501-1	BFI-S1
Residual indentation	EN ISO 24343-1(2.5h)	<0.1mm
Dimensional Stability	EN ISO 23999(80°C/6h)	<0.1%
Colour fastness	EN ISO 105-B02	≥6
Slip resistance	EN 13893	DS (>0.3)
Electrical propensity	EN1815	<2kv
Wear and scratch resistance	EN 16094	Pass with good result
Chemical resistance	EN ISO 26987	Pass with good result
Effect of castor chair	EN 425	Suitable
Underfloor heating		Ok (max +27°C)
Anti bacterial growth		Does not act as substrate

