

WINKEL PRO GUARD SECURING COMPOUND



Technical Bulletin

WINKEL PRO GUARD is conventional lacquer used for securing and identification. Soluble protection to guard against unknown interference, to cover electrically conductive parts, to protect against corrosion and to protect against interference by contact.

- Based on organic solvents
- Solvable Protection
- Protection against interference of third person
- To cover electrically conductive parts
- Very good adhesion
- Universally usable for many materials
- High isolation resistance

Technical properties uncured product

Viscosity ¹⁾ [s/mm]:	200 / 8
Evaporation time (depending on layer thickness) [min]:	20 at +25 °C
Application temperature [°C]:	+18 to +30
Colour:	blue/red

1) At 20 °C, Brookfield viscometer

Cured

Curing time (layer thickness 200 µm) [min]:	30
Temperature range [°C]:	-40 to +80

Storage & Durability

The shelf life is, at the optimum storage temperature of +5°C to +23°C in the closed original container, a maximum of 12 months. A higher storage temperature leads to a significantly lower durability. The storage temperature must not fall below +5°C.

Information about application

Surfaces must be dry and free of grease and dust. For this purpose use WINKEL PRO FAST CLEANER. The material's temperature should not be below +18 °C, because curing time will increase significantly. Coated part can be treated immediately.

Art. Nr. :	Packaging:
20801 Red	50 mL
20800 Blue	50 mL

IMPORTANT NOTICE: This information is presented to assist the user in determining whether our products are suitable for his intended application and user assumes all risks and liability whatsoever in connection therewith. No warranty or representation express or implied, shall apply to these products. Seller's only obligation shall be to replace quantity of this product which has proven to not substantially comply with the data presented Manufacturer's latest bulletin. Seller shall not be liable for any property loss or damage, direct or consequential, arising out of the use of or the inability to use the product. No protection from any law or patent is to be inferred and all patent rights are reserved. See Material Safety Data Sheet.