



# Technical Data Sheet

**AkzoNobel**  
Tomorrow's Answers Today

## Textura Design (Acrylic Texture Design)

**Description:** Acrylic Texture Design is a matt texture coating with small sand particles that provides decorative, delicate and sophisticated effects to the walls. Many different effects can be obtained according to the tools used. The product can be tinted to a variety of colours in the Tinting System. Alternatively, one can opt to apply the Texture in the White colour and topcoat it with an acrylic paint in the colour desired.

**Benefits:** Easy to apply, dispenses with the use of mortar on masonry surfaces, can be applied on interiors and exteriors.

**Tips:** Apply one coat of an acrylic paint in the same colour of the Texture Design as a priming coat. After the paint is dry, spread the Texture, undiluted and evenly over areas of up to 2m<sup>2</sup> and then make crisscross or circular movements with a trowel to obtain the final effect.

### Physical-Chemical Properties

**Colour:** White and tinting system.

**Consistency:** 9,0 - 10,0cm.

**Gloss (@60°):** N.A.

**Specific Weight:** 1,790 - 1,812g/cm<sup>3</sup>.

**Solids/Volume:** 57,4 - 61,4%.

**VOC (volatile organic compound):** 19,33 g/L.

**Solids/Weight:** 77,8 - 81,8%.

**Flashpoint:** >100° C.

### Technical Information

**Composition:** Styrene acrylic resin, inert pigments, aliphatic hydrocarbons, surfactants, coalescents, thickeners, non-metallic micro-biocides and water.

**Shelf life:** 24 months.

**Packaging:** 18L, 15L and 3,2L.

**Toxicity:** Low.

### Application Data

**Diluent:** Water.

**Thinning:** Ready for use. For application with a hard foam roller, dilute with up to 15% water.

**Spreading Rate:** 18L White: up to 28 m<sup>2</sup>/bucket/coat.

15L diluted: up to 23m<sup>2</sup>/bucket/coat. Undiluted: up to 14m<sup>2</sup>/bucket/coat.

3,2L diluted: up to 5m<sup>2</sup>/gallon/coat. Undiluted: up to 3m<sup>2</sup>/gallon/coat.

It varies depending on surface roughness or desired effect.

**Number of coats:** 1 coat.

**Tools:** Rubber roller,woolen roller, foam roller, steel trowel, scraper, brush, etc.

**Cleaning:** Clean tools with soap and water.

**Drying:** Touch: 1 hour.

**Recoating with paint if needed:** 4 hours.

**Final:** 4 days.

**Caution:** Avoid applying on rainy days, temperatures below 10°C or above 40°C and air relative humidity above 85%.



#### N.B.:

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience; however, we cannot guarantee the performance if the conditions are not respected. Rev.: 10/2015