



Technical Data Sheet

AkzoNobel
Tomorrow's Answers Today

Brilho para Tinta (Coral Gloss Liquid)

Description: The Gloss Liquid is a colourless liquid that provides gloss when applied over matt water-based paints in interior surfaces. However, if the intention is to regulate the level of gloss of a matt paint, mix the Gloss Liquid gradually to the last coat of the paint, for both interiors and exteriors.	
Benefits: The Gloss Liquid also provides waterproofing properties to the surface, makes cleaning easier, has low odour and dries fast.	
Other tips: The intensity of the gloss is controlled by the quantity of Gloss Liquid mixed to the paint (maximum 70% of Gloss Liquid and 30% of Paint). If applied over White paint, the colour may get slightly yellowish. When applied over coloured paint, the shades may get a little bit darker. In order to achieve an even gloss, we recommend to mix it with either Decora Acrylic Matt or Coralatex Acrylic Paint.	
Physical-Chemical Properties	
Colour: Clear.	Viscosity: 70 - 85 UK.
Gloss (@60°): N.A.	Specific Gravity: 1,010 - 1,110g/cm ³ .
Solids (by volume): 38,2 - 42,2%.	VOC (Volatile Organic Compound): 22,05g/L.
Solids (by weight): 39,0 - 43,0%.	Flash Point: 100° C.
Technical Information	
Composition: Modified acrylic resin, aliphatic hydrocarbons, surfactants, thickeners, non-metallic micro-biocides, other additives and water.	Shelf life: 24 months. Packaging: 3.6L and 18L.
Toxicity: Low.	
Application data	
Diluent: Water.	Dilution: As a finishing coat: 10 – 20% clean water. As a gloss regulator: 10-15% clean water mixed with the final coat of the paint.
Spreading rate: Up to 45 m ² /gallon 3.6L/coat.	Number of coats: As a finishing coat, apply 2 coats over the cured paint, minim 5 days.
Tools: Short-pile woolen roller or soft-bristled brush.	Cleaning: Wash tools with soap and water.
Drying time: 1 hour. Recoat: 4 hours. Final: 4 hours.	Recommendations: Avoid applying the paint during rainy days, temperatures below 10°C or above 40°C and air humidity above 85%.

N.B.:

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience; however, we cannot guarantee the performance if the conditions are not respected. Rev.: 03/2015

