



Technical Data Sheet

AkzoNobel
Tomorrow's Answers Today

Coral Wood Primer (*Coralit Fundo Nivelador*)

Product Description

Specially developed to ensure a uniform absorption on new wooden surfaces. For the preparation of external and internal new wooden surfaces.

Physicochemical Information

Colour: White

Viscosity: 80 - 88 KU

Dry Gloss (@60°): Not applicable

Specific Gravity: 1,270 - 1,310 g/cm³

Solids (by volume): 42,94 – 46,94%

VOC (volatile organic compounds): 330,36 g/L

Solids (by weight): 61,72 - 65,72%

Flash Point: 37° C

Technical Information

Composition: Alkyd resin, active or inert pigments, additives, aliphatic solvent.

Packaging: 3,6L , 900 mL

Expiration date: 36 months

Application data

Thinner: Mineral Turpentine

Number of coats: Normally 1 coat is enough. However, depending on the type of surface more coats may be required.

Thinning: Thin the product with solvent Mineral Turpentine up to 10% (brush) or 20% (spray gun).

Spreading Rate: Up to 34 m²/coat/gallon

Tools: Foam roller, brush or spray gun.

Drying time: To touch 4 a 6 hours; Recoat: 8 hours; Final: 12 - 20 hours.

Cleaning: Wash tools with Mineral Turpentine.

Recommendations: Avoid applying the paint during rainy days, temperatures below 10°C or above 40°C and air humidity above 85%.