



Technical Data Sheet

AkzoNobel
Tomorrow's Answers Today

Sparlack Extra Marine Varnish Satin

Product Description

Sparlack Extra Marine values the natural aspect of the wood, maintains the beauty of its veins and does not change the colour. Suitable for external and internal environments, such as doors, ceilings and wood.

Physicochemical Information

| | |
|------------------------------------------|---------------------------------|
| Colour: | Natural |
| Viscosity (CP4): | 40 - 50 seg |
| Dry Gloss (@60°): | Not applicable |
| Specific Gravity: | 0,905 – 0,945 g/cm ³ |
| Solids (by volume): | 38,09 – 42,09% |
| VOC (volatile organic compounds): | 476,71 g/L |
| Solids (by weight): | 46,47 – 50,47% |
| Flash Point: | 37°C |

Technical Information

Composition: Modified alkyd resins with polyurethane, UV rays absorber pigments, aliphatic and aromatic hydrocarbons solvents and additives.

Shelf life: 36 months

Packaging: 18L , 3,6L and 900 mL

Application data

| | |
|---------------------------|----------------------------------------------------------------------------------|
| Thinner: | Thin with Mineral turpentine. |
| Thinning: | Up to 10% for to apply with brush, roller and up to 30% to apply with spray gun. |
| Coverage per coat: | 70 to 110 m ² /coat/gallon |
| Number of coats: | New wood: 3 coats. |

Repainting: 1 or 2 coats.

Tools:

Brush, roller and spray gun

Cleaning:

For tools use Mineral Turpentine.

Drying time:

To touch: 2 hours; Handling: 8 hours;

Between coats: 8 to 12 hours; Final: 24 hours.

Recommendations:

Avoid applying the paint during rainy days, temperatures below 10°C or above 40°C and air humidity above 85%.