

## Technical Data Sheet

### Secondary Insulation

# **Pedigree<sup>®</sup> 6180 VT**

(6180 Polyester Resin)

## Polyester Impregnating Resin

**ELANTAS PDG, Inc.**  
5200 North Second Street  
St. Louis, MO 63147  
USA  
Tel +1 314 621-5700  
Fax +1 314 436-1030  
info.elantas.pdg@altana.com  
www.elantas.com

## Pedigree® 6180 VT

### Product Description

Pedigree® 6180 VT is a 100%-reactive, unsaturated polyester resin in vinyl toluene monomer. It requires the addition of a peroxide catalyst for proper cure.

### Areas of Application

Impregnation of motor windings including stators and high-speed armatures

### Features and Benefits

- Chemically promoted for low temperature cure
- Low viscosity
- High bond strength at elevated temperature
- 3 day catalyzed pot life
- UL recognized insulation systems up to Class 240

### Application Methods

- Trickle
- Dip-and-Bake

### Transportation / Storage

Store below 25°C / 77°F in a dry controlled environment out of direct sunlight. This material should be suitable for use stored under these conditions in the original sealed containers for two (2) months from the date of shipment.

Failure to store this product as recommended above may lead to deterioration in product performance.

Keep containers tightly sealed to minimize evaporation. Refrigeration is recommended for long term storage.

Mix product thoroughly before use

See Technical Bulletin TI-4001 for tank maintenance instructions

### Health / Safety

Refer to the Material Safety Data Sheet.

### Typical Properties of Material as Supplied

Property	Conditions	Value	Units
Viscosity	25°C / 77°F	150 - 200	cP
Gel Time	100°C / 212°F	8 – 15	minutes
Catalyst	2% by weight	ELAN-Plus™ C 8 Catalyst	
Viscosity Reducer		ELAN-Plus™ BS-217 Diluent	
Gel Time Adjuster		ELAN-Plus™ BS-6440 Inhibitor	
Weight per Gallon	25°C / 77°F	8.8 – 9.2	pounds
Flash Point	ASTM D93	46 115	°C °F

## Pedigree® 6180 VT

### Application / Curing Schedule

Add ELAN-Plus™ C 8 Catalyst in amount specified above and mix thoroughly.

Apply resin by trickle or dip.

Cure for 30 minutes at 82°C / 180°F - or - 20 minutes at 93°C / 200°F.

Cure schedule is based on time after unit reaches specified temperature.

### Typical Mechanical Properties

Property	Conditions	Value	Units
Twisted Coil Bond Strength ASTM D2882 over MW 35	25°C / 77°F	28	pounds
	150°C / 302°F	26	pounds
Hardness	Shore D	85 - 90	

### Typical Electrical Properties

Property	Conditions	Value	Units
Dielectric Strength	ASTM D149 – 1.5 mils	3400	volts/mil

### UL Recognized Insulation Systems (ELANTAS File E87039)

Thermal Class	System
Class 130	PDG 1, 2, 6, 12, 106, 107, 110, 111
Class 155	PDG 3, 9, 102, 108, 86-155-1
Class 180	PDG 14, H-1, 91-180-1, 86-180-5
Class 200	PDG 7, 10
Class 220	PDG 15
Class 240	PDG 16

The above properties are typical values and are not intended for specification use.

ELANTAS PDG, Inc. warrants the chemical composition of its products within stated tolerances, but does not guarantee that a product will be appropriate for any particular application. Any recommendation, performance of tests or suggestion is offered merely as a guide and is not a substitute for a thorough evaluation by the user. No representative of ELANTAS PDG, Inc. has the authority to offer a warranty that a product will perform satisfactorily in manufacturing a product and no such representation should be relied upon.