

# Insulthane® 500 HY-LE

## Insulthane® 500 HY-LE

Insulthane® 500 HY is a two component, light density, open-cell spray polyurethane foam insulation system. The high expanding formula provides economical yield and impressive air-sealing qualities to reduce heat loss through air infiltration. Due to the lighter density, Insulthane 500 HY has added sound-dampening properties, helping to create a quieter indoor environment.

#### **Thermal Resistance**

| Thickness (inch) | R-Value (°F·ft²·h/Btu) |
|------------------|------------------------|
| 1.0              | 3.9                    |
| 2.0              | 7.8                    |
| 3.5              | 13                     |
| 4.0              | 15                     |

## **Features**



## **High Expansion**

Expands to seal common gaps & crevices



#### Water Blown

Elimate harmful chemicals with a water-blown system



#### **Noise Reduction**

Minimize noise with a sound-absorbing formula



## **Cost Savings**

Prevents air leaks to reduce energy loss

## **Physical Properties**

| Attribute   | Test       | Results                    |
|---|------------|----------------------------|
| Density   | ASTM D1622 | 0.5 lb/ft³                 |
| Open-Cell Content<br>(Procedure 2)                    | ASTM D6226 | 100%                       |
| Dimensional Stability<br>(Volume Change after 7 days) | ASTM D2126 | -0.1% @ 158°F<br>& 97% RH  |
| Water Vapor<br>Transmission @2"                       | ASTM E96   | 27.6 perms                 |
| Air Permeance   | ASTM D6226 | 0.0028 cfm/ft <sup>2</sup> |
| Water Absorption (% Volume)                           | ASTM D2842 | 6.7%                       |
| Re-entry - worker                                     | ASTM D8445 | 1 hour                     |
| Re-occupancy  |            | 1 hour                     |
| Material Listing                                      | Intertek   | CCRR-0396                  |

### **Burn Characteristics**

| Attribute                                  | Test     | Results               |
|--|----------|-----------------------|
| Flame Spread                               | ASTM E84 | 20                    |
| Smoke Development                          | ASTM E84 | 215                   |
| Surface Burning<br>Characteristics @ 1"    | ASTM E84 | Class 1 (A)           |
| Unvented Attic WIthout<br>Ignition Barrier | UVA      | Walls 18"<br>Roof 18" |

## **Application Areas**

Interior walls, attics, floors, crawlspaces, ceilings





