

UR5117

Polyurethane Resin

UR5117 is an ultra-high performance resin system with excellent resistance to water. UR5117 can be supplied in bulk or resin pack form.

- Low moisture sensitivity during cure and exhibits good adhesion to most substrates
- Very low viscosity; allows ease of potting of difficult and complex geometries
- High toughness and tear resistance; low temperature flexibility to -60°C
- Excellent oxidation resistance; low water absorption and high resistance to sea water


Approvals	RoHS Compliant (2015/863/EU):	Yes
	UL Approval:	No
Typical Properties		
Liquid Properties:	Base Material	Polyurethane
	Density Part A - Resin (g/ml)	0.92
	Density Part B - Hardener (g/ml)	1.22
	Part A Viscosity (mPa s @ 23°C)	3390
	Part B Viscosity (mPa s @ 23°C)	150
	Mixed System Viscosity (mPa s @ 23°C)	3200
	Mix Ratio (Weight)	2.77:1
	Mix Ratio (Volume)	3.66:1
	Usable Life (20°C)	25-30 mins
	Gel Time (23°C)	35-45 mins
	Cure Time (23°C)	36 hours
	Cure Time (60°C)	4 hours
	Colour Part A - Resin	Black
	Colour Part B - Hardener	Brown
	Storage Conditions	Dry Conditions: Above 15°C, Below 30°C
	Shelf Life	12 Months
	Exotherm	< 50°C
	(Measured on 100ml sample in a cylinder of diameter 49.4mm @ 20-25°C)	< 0.5%
	Shrinkage	

Cured System:	Thermal Conductivity (W/m.K)	0.20
	Cured Density (g/ml)	0.99
	Temperature Range (°C)	-60 to +120
	Max Temperature Range (Short Term (°C)/30 mins) (Application and Geometry Dependent)	+130
	Dielectric Strength (kV/mm)	18
	Volume Resistivity (ohm-cm)	10^{15}
	Shore Hardness	A80
	Colour (Mixed System)	Black
	Flame Retardancy	No
	Loss Tangent @ 50 Hz	0.01
	Permittivity @ 50 Hz	3.10
	CTE	150 ppm/°C
	Water Absorption (9.7mm thick disk, 51mm diameter) 10 days @ 20°C / 1 hour @ 100°C	< 0.5% / < 1%
	Elongation At Break	50%
	Tensile Strength	5.5 MPa
	Tear Strength	0.99 MPa
	Halide content	4 ppm
	Sulphur content	≤ 1 ppm

Mixing Procedures

Resin Packs

When in Resin pack form, the resin and hardener are mixed by removing the clip and moving the contents around inside the pack until thoroughly mixed. To remove the clip, remove both end caps, grip each end of the pack and pull apart gently. By using the removed clip, take special care to push unmixed material from the corners of the pack. Mixing normally takes from three to four minutes depending on the skill of the operator and the size of the pack. Both the resin and hardener are evacuated prior to packing so the system is ready for use immediately after mixing. The corner may be cut from the pack so that it may be used as a simple dispenser. There is also a YouTube video ([Polyurethane Mixing Instructions](#)) available on the Electrolube channel to show the mixing process.



Bulk Mixing

When mixing, care must be taken to avoid the introduction of excessive amounts of air. Automatic mixing equipment is available which will not only mix both the resin and hardener accurately in the correct ratio but do this without introducing air. Containers of Part A (Resin) and Part B (Hardener) should be kept sealed at all times when not in use to prevent the ingress of moisture. Bulk material must be thoroughly mixed before use. Incomplete mixing or use of the wrong mix ratio will result in erratic or partial curing.

Additional Information

Cleaning: It is far easier for machines & containers to be cleaned before the resin has been allowed to cure. Electrolube's RRS is suitable for cleaning machines and containers and cured resin may be slowly softened and removed by soaking in our RRS.

Curing: Do not heat cure large volumes immediately. Allow these to gel at room temperature and post-cure at high temperature if required (refer to liquid properties for details). Small volumes (250ml) may be heat cured immediately.

Storage: When storing under very cold conditions, the hardener may crystallise. If this occurs, simply warm (40°C) the container gently until all crystals have re-melted.

Health & Safety: Always refer to the Health & Safety data sheet before use. These can be downloaded from www.electrolube.com

Revision 4: Mar 2019