

## ER2091 Epoxy Resin

ER2091 is a flame retardant, two-part epoxy with a low hydrolysable chlorine content. The low chlorine level gives rise to excellent electrical properties and the cured material meets the requirements of UL94 V-0.

- Low hydrolysable chlorine content; excellent electrical properties
- Excellent adhesion to a wide variety of substrates, including metals, plastics and ceramics
- Good performance in changing thermal environments; reduces risk of damaging sensitive components
- Flame retardant resin; meets UL94 V-0

<b>Approvals</b>	<b>RoHS Compliant (2015/863/EU):</b>	<b>Yes</b>
	<b>UL Approval:</b>	<b>No</b>

### Typical Properties

Liquid Properties:	Base Material	Epoxy
	Density Part A - Resin (g/ml)	1.85
	Density Part B - Hardener (g/ml)	0.87
	Part A Viscosity (mPa s 23°C)	600,000
	Part B Viscosity (mPa s 23°C)	250
	Mixed System Viscosity (mPa s 23°C)	16,000
	Mix Ratio (Weight)	20.76:1
	Mix Ratio (Volume)	9.73:1
	Usable Life (20°C)	2 hours
	Gel Time (25°C)	7 hours
	Cure Time (25 °C)	24 hours
	Cure Time (80 °C)	1 hours
	Cure Time (100 °C)	30 minutes
	Colour Part A - Resin	Off-White
	Colour Part B - Hardener	Amber
	Storage Conditions	Dry Conditions: Above 15°C, Below 35°C
	Shelf Life	24 Months (bulk)

#### Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,  
Ashby de la Zouch,  
Leicestershire LE65 1JR

T +44 (0)1530 419 600

F +44 (0)1530 416 640


BS EN ISO 9001:2008  
Certificate No. FM 32082

Cured System:	Thermal Conductivity (W/m.K)	0.60
	Cured Density (g/ml)	1.76
	Temperature Range (°C)	-40 to +130
	Max Temperature Range (Short Term (°C)/30 Mins) (Application and Geometry Dependent)	+150
	Dielectric Strength (kV/mm)	11
	Volume Resistivity (ohm-cm)	10 <sup>14</sup>
	Shore Hardness	D80
	Colour (Mixed System)	Off White
	Flame Retardancy	Meets UL94 V-0
	Tensile Strength (MPa)	30
	Compressive Strength (MPa)	80
	Deflection Temperature (°C)	60
	Coefficient of Expansion (ppm/°C)	35
	Loss Tangent @ 50 Hz	0.07
	@ 1 kHz	0.03
	@ 1 MHz	0.02
	Permittivity @ 50 Hz	6.0
	@ 1 kHz	5.5
	@ 1 MHz	4.8
	Comparative Tracking Index	>800V

## **Mixing Procedures**

### **Resin Packs**

When in Resin pack form, the resin and hardener are mixed by removing the clip and moving the contents around inside the pack until thoroughly mixed. To remove the clip, remove both end caps, grip each end of the pack and pull apart gently. By using the removed clip, take special care to push unmixed material from the corners of the pack. Mixing normally takes from three to four minutes depending on the skill of the operator and the size of the pack. Both the resin and hardener are evacuated prior to packing so the system is ready for use immediately after mixing. The corner may be cut from the pack so that it may be used as a simple dispenser. There is also a YouTube video ([Epoxy Mixing Instructions](#)) available on the Electrolube channel to show the mixing process.



Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,  
Ashby de la Zouch,  
Leicestershire LE65 1JR

T +44 (0)1530 419 600

F +44 (0)1530 416 640

BS EN ISO 9001:2008  
Certificate No. FM 32082

### **Bulk Mixing**

When mixing, care must be taken to avoid the introduction of excessive amounts of air. Automatic mixing equipment is available which will not only mix both the resin and hardener accurately in the correct ratio but do this without introducing air. Containers of Part A (Resin) and Part B (Hardener) should be kept sealed at all times when not in use to prevent the ingress of moisture. Bulk material must be thoroughly mixed before use. Incomplete mixing or use of the wrong mix ratio will result in erratic or partial curing.

### **Additional Information**

- Cleaning:** It is far easier for machines & containers to be cleaned before the resin has been allowed to cure. Electrolube's RRS is suitable for cleaning machines and containers and cured resin may be slowly softened and removed by soaking in our RRS.
- Storage:** When storing under very cold conditions, the hardener may crystallise. If this occurs, simply warm (40°C) the container gently until all crystals have re-melted.
- Health & Safety:** Always refer to the Health & Safety data sheet before use. These can be downloaded from [www.electrolube.com](http://www.electrolube.com)

Revision 2: Mar 2019