TYPE	HEAT TREATMENT
8620	**NORMALIZED 1700° F. — AUSTENITIZED 1700° F.**

CHEMICAL ANALYSIS	C	Mn	P	S	Si	Cr	Ni	Mo	Cu	Al	V	W	B
	.20	.85	.010	.014	.30	.50	.51	.19	.09	.031	—	—	—

ROUND SECTION WITH SAME HARDNESS AT MID-RADIUS