


1 X 7 + 6 X 7



Rope diameter mm.	Diam. Out. Wire mm.	Steel cross section mm <sup>2</sup>	Min. Breaking Load kgf.	Weight Kg./mt
6,00	0,65	16,25	2.325	0,142
8,00	0,85	27,79	4.133	0,250
9,00	1,00	38,47	5.231	0,320
10,00	1,10	46,54	6.458	0,400
12,00	1,30	65,01	9.300	0,570

IWRC + 6 X 19 Standard




Rope diameter mm.	Diam. Out. Wire mm.	Steel cross section mm <sup>2</sup>	Min. Breaking Load kgf.	Weight Kg./mt
8	0,50	26,10	3.823	0,243
9	0,60	37,59	4.839	0,308
10	0,65	44,11	5.974	0,381
11	0,70	51,16	7.229	0,461
12	0,75	58,73	8.603	0,548
13	0,85	75,43	10.096	0,643
14	0,90	84,57	11.709	0,746
16	1,05	115,11	15.294	0,974
18	1,15	138,08	19.356	1,230
20	1,30	176,44	23.897	1,520
22	1,45	219,51	28.915	1,840
24	1,55	250,83	34.411	2,190
26	1,70	301,73	40.386	2,570

FC + 6 X 19 Seale



Rope diameter mm.	Diam. Out. Wire mm.	Steel cross section mm <sup>2</sup>	Min. Breaking Load kgf.	Weight Kg./mt
12	0,96	57,03	8.577	0,537
13	1,04	66,93	10.066	0,630
14	1,12	77,63	11.674	0,730
15	1,20	89,11	13.401	0,838
16	1,28	101,39	15.248	0,954
17	1,36	114,46	17.213	1,077
18	1,44	128,32	19.298	1,207
19	1,52	142,98	21.502	1,345
20	1,60	158,42	23.825	1,490
21	1,68	174,66	26.267	1,643
22	1,76	191,69	28.828	1,803

IWRC + 6 X 19 Seale



Rope diameter mm.	Diam. Out. Wire mm.	Steel cross section mm <sup>2</sup>	Min. Breaking Load kgf.	Weight Kg./mt
10	0,80	46,13	7.000	0,410
12	0,96	66,43	10.150	0,590
14	1,12	90,41	13.900	0,810
16	1,28	118,09	18.300	1,060
18	1,44	149,46	23.000	1,330
20	1,60	184,52	28.400	1,640
22	1,76	223,27	34.400	1,990
24	1,92	265,71	40.700	2,350
26	2,04	311,84	47.900	2,770

FOLLOWING CLIENT'S NEEDS, REMER IS ABLE TO PRODUCE THE OVER - DISPLAYED WIRE ROPES IN ALL REQUESTED DIAMETERS.

