

Emission Test Certificate

Wednesday, 7th March 2018

Supplier: Godfrey Hirst Australia Pty Ltd (7 Factories Road, Geelong, VIC, 3220)

Sample Description: GH Hybrid 5.8mm/0.3mm Wear Layer Flooring

Date Tested: February 2018 (Tested by FORAY Laboratories – NATA Accreditation 1231)

Test Method: ASTM D5116-17 “Standard Guide for Small-Scale Environmental Chamber Determinations of Organic Emissions from Indoor Material/Products”.

Emission Data (24 hrs exposure):

Global GreenTag	GH Hybrid 5.8mm/0.3mm Wear Layer Flooring
Total Volatile Organic Compound Emission Rate limit: <0.5 mg/m ² /hr	Total Volatile Organic Compound Emission Rate: 0.052 mg/m ² /hr
4-phenylcyclohexene Emission Rate Limit: <0.05 mg/m ² /hr	4-phenylcyclohexene Emission Rate: <0.004 mg/m ² /hr
Formaldehyde Emission Rate limit <0.1 mg/m ² /hr	Formaldehyde Emission Rate: 0.010 mg/m ² /hr



Dr. Vyt Garnys
PhD, BSc(Hons) AIMM, ARACI, ISIAQ
ACA, AIRAH, FMA
Managing Director and Principal Consultant



Nick Joy
BSc(Hons)
Consultant



Tuan Duong
B Eng. (Chem.)
Consultant

CV180249