

ALPHA CHEM X150

LIMITED LIFE CHEMICAL COVERALL

Alphachem X150 is a light, durable and cost effective disposable chemical protective garment manufactured using lightweight HDPE fabric.

BENEFITS

- ▲ Designed to provide increased wearer comfort, exceptional levels of safety and protection, with superior durability
- ▲ Double sleeve system with inner thumb loop
- ▲ Improved fit, enhanced freedom of movement with two piece crotch pattern
- ▲ 3 piece hood ensures a comfortable fit
- ▲ Double zip / grab tag - easier to hold when wearing gloves
- ▲ Knee patches give extra re-enforcement where it's needed most
- ▲ Stitched and taped seams provide a strong and effective chemical barrier
- ▲ Quick and easy donning/doffing
- ▲ Elasticated ankles and wrists ensure a snug and secure fit

EN STANDARDS



EN 14605+
A1:2009



EN 1149-5:
2018



EN 1073-2:
2002
Class 1



EN ISO 13982-1:
2004 + A1:2010
Type 5



ISO 27065:
2017+A1:2019



EN 14605+
A1:2009
Type 3



EN 14605
+A1:2009
Type 4



EN 13034:
2005+A1:2009
Type 6



EN 14126:
2003
Type 3B, 4B,
5B & 6B

US TESTING DATA

Property	Test Method	Typical Value
Basis Weight	ASTM D3776	2.18 oz/yd ²
Tear Resistance—Trap Tear, MD	ASTM D1117	9.1 lbf
Tear Resistance—Trap Tear, CD	ASTM D1117	18.2 lbf
Breaking Strength—Grab, MD	ASTM D5034	38.7 lbf
Breaking Strength—Grab, CD	ASTM D5034	26.0 lbf
Hydrostatic Head	AATCC 127	53.8 inches H ₂ O

Tested to ASTM D257 & AATCC 76.



SUITABLE APPLICATIONS

Offers chemical resistance against splashes and sprays of hazardous chemicals in Type 3, 4 and 6 applications.

- ▲ Agriculture
- ▲ Chemical Spills
- ▲ Decontamination Work
- ▲ Pest Control
- ▲ Plant Maintenance
- ▲ Pressure Cleaning
- ▲ Tank Cleaning

ALPHACHEM X150

Limited life chemical coverall

TECHNICAL SPECIFICATIONS

FABRIC PHYSICAL TESTS ACCORDING TO EN 14325: 2004		
Test Method	Result	EN Class
Abrasion Resistance EN530 Method 2	>100 <500 cycles	2 of 6
Flex ISO 7854 Method B	>100 <2,500 cycles	1 of 6
Tear Resistance EN ISO 9073-4 (MD)	85.5 N	4 of 6
Tear Resistance EN ISO 9073-4 (CD)	39.1 N	2 of 6
Tensile Strength ISO 13934-1 (MD)	140.0 N	3 of 6
Tensile Strength ISO 13934-1 (CD)	61.0 N	2 of 6
Puncture Resistance EN 863 11.0 N	11.0 N	2 of 6

OTHER PHYSICAL PERFORMANCE DATA	
Description	Result
BS EN 20811 Resistance to Water Penetration	>22 kPa
ISO 13938-1 Bursting Resistance	61.6 kPa Class 1 of 6
EN 25978 Resistance to Blocking	No Blocking
EN1149-5: 2018 Electrostatic Surface Resistance	PASS - Half Decay t50 = 0.05s
EN 14362-1 Arylamines derived from Prohibited Azo Dyes	None Detected
EN ISO 3071:2006 pH of Aqueous Extract	PASS


FABRIC CHEMICAL PERMEATION EN 374-3: 2003 1.0 µg / CM² / MIN		
Chemical	Result	EN Class
Sulphuric Acid 98% Material	>480 min	6 of 6
Sodium Hydroxide 48% Material	>480 min	6 of 6
Sulphuric Acid 98% Taped Seam	>480 min	6 of 6
Sodium Hydroxide 48% Taped Seam	>480 min	6 of 6

OTHER PHYSICAL PERFORMANCE DATA							
Chemical Permeation Data	Additional Tests	Generic Representation	MDPR µg/cm2/min	BDT Minutes	SBT (Minutes) 1.0µg/cm2/min	NBT (Minutes) 1.0µg/cm2/min	EN Class
Chemical	CAS Number						
Acetone (99.9 wt%)*	67-64-1	Ketone	0.02	>480	>480	>480	6 of 6
Acetonitrile (99.99 wt%)*	75-05-8	Nitrile Compound	0.02	>480	>480	>480	6 of 6
Ammonia Hydroxide (25% wt%)	1336-21-6	Aqueous Ammonia	0.04	<1	<1	<2	0
Acrylic Acid (90%v/v)	79-10-7	Unsaturated Organic Acid	0.05	7	11	51	2 of 6
Diesel Fuel >99wt%	68334-30-5	Hydrocarbon Liquid	0.05	6	8	16	1 of 6
Hydrochloric Acid 37wt%	7647-01-0	Inorganic Acid	0.05	183	381	425	5 of 6
Hydrofluoric Acid 48-51wt%*	7664-39-3	Inorganic mineral acid	0.03	36	372	>480	6 of 6
Hydrofluoric Acid 58-62wt%#	7664-39-3	Inorganic mineral acid	0.03	9	88	419	5 of 6
Isopropyl Alcohol (99.99 wt%)*	67-63-0	Secondary Alcohol	0.02	>480	>480	>480	6 of 6
Kerosene	8008-20-6	Hydrocarbon Liquid					EBT>480mins
Methanol (99.99 wt%)*	67-56-1	Primary Alcohol	0.06	>480	>480	>480	6 of 6
Nitric Acid (60wt%)	7697-37-2	Inorganic mineral acid	0.03	5	353	>480	6 of 6
Phenol (liquified 89% in water)	108-95-02	Aromatic Organic	0.02	>480	>480	>480	6 of 6
Phosphoric Acid > 85wt%	7664-38-2	Inorganic Acid	0.05	>480	>480	>480	6 of 6
Potassium Hydroxide (80%wt%)	1310-58-3	Inorganic alkali	0.005	>480	>480	>480	6 of 6
Sodium Hydroxide (48wt%)*	1310-73-2	Inorganic alkali				>480	6 of 6
Sodium Hypochlorite (10-15% Active Cl)*	7681-52-9	Liquid Bleach	0.05	>480	>480	>480	6 of 6
Sulphuric Acid (98 wt%)*	7664-93-9	Inorganic mineral acid				>480	6 of 6
Titanium Tetrachloride (99.5wt%)	7550-45-0	Inorganic volatile liquid	0.08	-	2	7	0
Titanyl Chloride (<32wt%)	13780-39-7	Reducing Agent	0.08	>480	>480	>480	6 of 6

MDPR = Minimum Detectable Permeation Rate
 BDT = Breakthrough detection time (first appearance at the minimum detectable permeation rate) ASTM F739-12
 SBT = standardized breakthrough time (at 0.1 µg/cm2/min). ASTM F739-12
 NBT = Normalized breakthrough time (at 1.0 µg/cm2/min). EN 16523-1:2015
 The permeation data published have been generated by independent accredited testing laboratories according to the specified test methods. The data is typically the average of three fabric samples tested unless otherwise stated.
 * Denotes tests also carried out on seam and results equivalent to or greater than material, only, test results.
 # Denotes mean of six measured samples.

EN 14126: 2003 - Barrier to Infective Agents		
Test Method	Result	EN Class
ISO 16603 - Resistance to penetration by blood/fluids under pressure	Pass to 20 kPa	6 of 6
ISO 16604 - Resistance to penetration by blood borne pathogens	Pass to 20 kPa	6 of 6
EN ISO 22610 - Resistance to wet bacterial penetration (mechanical contact)	Penetration >75 mins No Penetration	6 of 6
ISO/DIS 22611 - Resistance to biologically contaminated aerosols	Penetration Ratio Log 10 CFU >5 No Penetration	3 of 3
ISO 22612 - Resistance to dry microbial penetration	Penetration Log Log10 CFU < 1 No Penetration	3 of 3

SIZING Body Measurements



STORAGE AND MAINTENANCE

AlphaChem X150 is manufactured from materials made from polypropylene and polyethylene. These inert polymers are proven not to degrade within 10 years. Therefore a product shelf life of 10 years should be reasonable in correct storage conditions. It is advised to keep products stored in cool, dry areas where possible and away from direct heat and sunlight.

ORDERING INFORMATION

Part Number: X150



ALPHA SOLWAY LTD, Factory 1, Queensberry Street, Annan, DG12 5BL, UK
 T: +44 (0)1461 202 452 | E: sales@globusgroup.com | www.globusgroup.com



© 2023 Alpha Solway Ltd - Please note that all information given in this document is intended to be useful and informative and is correct to the best of our knowledge at time of print. No liability can be accepted for inaccuracies or omissions. The right is reserved to amend this information without prior notice. All our technical files, style descriptions, presentations, designs and drawings, give the latest update of the standards and design or style features of each product. However, delivered products may comply with previous standards, design or style features. For that Alpha disclaims any liability whatsoever. Contact our sales for full information if specific requirements are needed.