

Technical Data Sheet

HW2900 Castres PurePlank 06

Usage: See Havwoods guick reference guide to choosing the correct floor

Installation Methods

Fully Bonded	No
Nailed	No
Floated on underlay	Yes* (no underlay required)
Over Underfloor Heating	Yes*# (Please ask for our technical guidelines)

Grading Criteria

Typically, prime grade has few, if any knots, and these will be of minimal size. There will also be a minimal amount of sapwood and filler, if any at all. Where filler is used its colour is selected to complement the wood rather than to match it exactly and the colour of the filler may vary from batch to batch. There will be a relatively small amount of colour variation in the timber itself.

N.B. The product grading criteria is inspected at each mill visually and should be taken as an approximation only. Please ask for further details

Technical Criteria

Origin	Europe
Responsible Certification	FSC® Certified (FSC-C009500)
Janka Hardness Rating	1,120 lbf (4,980N)
Formaldehyde Emission	0.02 ppm - TSCA VI Compliant
Slip testing	91/28 PTV (CEN/TS 15676:2007)
Critical Radiant Flux	Class 1 - ASTM E 648
Thermal Conductivity	λ 0.20 W/m K (EN 12664)





The mark of responsible forestry

^ Please note that this is a smoked/fumed product. This reactive process will typically generate a wider range of colour variation in the product. * Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

Comprehensive maintenance instructions and materials are available from Havwoods for all floors.

- ** This product may require on-site sanding prior to applying a suitable finish
- # Temperature of top-face must never be allowed to exceed 27°C. UFH protocol to control temperature conditions is recommo

Fack lengths will either 1950mm of 2400mm dependant upon stock availability. Installation and Warranty: All Havwoods floor must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent standards worldwide.

This technical data sheet was written by Havwoods International. At the time of writing and publciation of the s information is specified correctly. The company reserves the right to change the specifications of this product time without prior notice to third parties. The photographs use in the sheet are intended only as illustrations. N can be derived from them.



Havwoods International (North America) 151 W 18th St, New York, NY 1011, USA

Tel - 1 347 523 8930 (WOOD) www.havwoods.com/us

European Oak (Quercus Robur)

0.6mm European Oak (Quercus Robur) Integral Cork backing (Cork)

1-Strip Brushed

Matt Lacquered

4-Sided Bevelled Edge

Click System


9mm (3/8")

2.057m²

Prime

190mm (7 1/2") 1203mm (7 1/2") (Fixed length)

Version 2



Specie

Pattern

Process Finish

Profile

Edge Profile

Top Layer

Backing

Width

Length

Grade

Pack Size

Maintenance

Thickness