



## TECHNICAL DATA SHEET

### HW7376T ANTIQUE OAK TWIST

#### PAR-KY

USAGE: SEE HAVWOODS QUICK REFERENCE GUIDE TO CHOOSING THE CORRECT FLOOR.



The photographs used in this sheet are intended only as illustrations, colours shown are only as accurate as the printing process or device screen will allow. Due to the size of this photograph, it does not provide any indication of grading. Please refer to our separate grading rules. No rights can be derived from them.

#### PRODUCT DETAILS

Product Code	HW7370T
Product Range	Par-ky
Construction	Engineered
Species	European Oak
Pattern	Herringbone Pattern
Process	Brushed
Finish	Matt Lacquered
Profile	Click System
Edge Profile	Micro-bevelled Edge
Top Layer	0.6mm European Oak Lamella
Backing	HDF core with real wood backing
Thickness	12mm
Width	124mm
Length	868mm
Grade	Prime
Maintenance	Comprehensive maintenance instructions and materials are available from Havwoods Ltd. for all floors. Contact your Havwoods consultant on 1300 428 966.

#### INSTALLATION METHODS

Fully Bonded	Yes
Nailed	No
Floated on underlay	Yes* (Recommended)
Over Underfloor Heating	Yes*# (to be installed over Wet Underfloor Heating Systems only. Please see UFH Installation Guidelines for details)

#### GRADING CRITERIA

Prime grade typically has few, if any knots, and these will be of minimal size. There will also be a minimal amount of sapwood defects and filler, if any at all. Where filler has been used, its colour is carefully selected to compliment the wood rather than to match it exactly and the colour of the filler may vary from batch to batch. There will be a relatively small amount of colour variation in the timber itself for Prime grade.

NB: The product grading criteria is an approximation only. Please ask for details. Contact your Havwoods consultant on 1300 428 966.

#### TECHNICAL CRITERIA

Origin	Europe
Janka Hardness Rating	1,120 lbf (4,980N)
Formaldehyde Emission	E1 (EN 717-1)
Pentachlorophenol Emission	PCP Free
Slip Testing	P3
Reaction to Fire Certification	Cfl-s1 (EN 13501-1)
Thermal Conductivity	$\lambda$ 0.230 W/m K

#### HAVWOODS SYDNEY SHOWROOM

28 Margaret Street  
Sydney CBD, NSW 2000



#### HAVWOODS MELBOURNE SHOWROOM

215 Roden Street  
West Melbourne, VIC 3003

#### HAVWOODS NEWCASTLE SHOWROOM

150 King Street  
Newcastle, NSW 2300

1300 428 966 | [info@havwoods.com.au](mailto:info@havwoods.com.au)

[www.havwoods.com.au](http://www.havwoods.com.au)

\* Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

# Temperature of top-face must never be allowed to exceed 27°C. Under Floor Heating (UFH) protocol to control temperature conditions is recommended.

#### INSTALLATION AND WARRANTY

All Havwoods floors must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent standard worldwide.

© This technical data sheet was written by Havwoods Limited, Carnforth Business Park, Oakwood Way, Carnforth Lancashire LA5 9FD. At the time of writing and publication of the sheet, all information is specified correctly. The company reserves the right to change the specifications of this product at any time without prior notice to third parties. The photographs used in this sheet are intended only as illustrations, colours shown are only as accurate as the printing process or device screen will allow. No rights can be derived from them.

