

## **TECHNICAL DATA SHEET**

# **HO924** TREKKER VULCAN GROOVED USAGE: COMMERCIAL AND RESIDENTIAL APPLICATIONS

(See Havwoods Quick Reference Guide to choosing the correct floor).



## TREKKER VULCAN GROOVED

PRODUCT DETAILS		
Product Reference	HO924	
Width x Thickness	143x22mm	
Board Type	Wood/Resin Composite	
Pattern	1-Strip Plank	
Length	3.2m	
Composition	Wood Flour/Polymer	
Maintenance	Comprehensive cleaning and maintenance instructions and materials are available from Havwoods Ltd. for all floors.	

### **INSTALLATION METHODS**


Fully Bonded	No		
Fixing	Clips and screws are included (please ask a member of staff for details)		
Floated on underlay	No		
Over Under Floor Heating	No		
Origin:	Europe		

Requirements –EN 15534-4	Result	
Declaration	0.31%	
Declaration	0.06mm	
Declaration	1459 Kg/m³	
≥ 36	60 PTV (Dry) 46 PTV (Wet)	
	Bfl-s1	
≤ 0.5mm	Max 0.12mm	
F¹ Max3300N (Mean) F¹ Max3000N (Individual) Deflection underload (mean) Deflection underload (individual)	4727N 4595N 1.1mm 1.2mm	
Absorption (Mean) ≤ 4% (thickness) ≤ 0.8% (width) ≤ 0.4% (length)	1.18% 0.23% 0.08%	
Absorption (Individual) ≤ 4% (thickness) ≤ 1.2% (width) ≤ 0.6& (length) Mean Absorption-7% Individual Maximum-7%	0.25% 0.13% 1.18%	
≤ 7% (mean)	1.42%	
Declaration	40%/60% Wood 40%/60% Polymer 10% Others	
Declaration	85.2°C	
Declaration	74°C	
≤50 x 10-6K	2.79 x10-5mn/mm°C	
Declaration	ΔL *5	
Declaration	EN15534-4 P/C W 50 UC3	
	Declaration  Declaration  Declaration  ≥ 36  ≤ 0.5mm  F¹ Max3300N (Mean)  F¹ Max300N (Individual)  Deflection underload (mean)  Deflection underload (individual)  Absorption (Mean)  ≤ 4% (thickness)  ≤ 0.8% (width)  ≤ 0.4% (length)  Absorption (Individual)  ≤ 4% (thickness)  ≤ 1.2% (width)  ≤ 0.6& (length)  Mean Absorption - 7%  Individual Maximum - 7%  ≤ 7% (mean)  Declaration  Declaration  Declaration	Declaration         0.31%           Declaration         0.06mm           Declaration         1459 kg/m³           ≥ 36         60 PTV (Dry) 46 PTV (Wet)           Bfl-s1         60 PTV (Wet)           ≤ 0.5mm         Max 0.12mm           F¹ Max 3300N (Mean)         4727N           F¹ Max 3000N (Individual)         4595N           Deflection under load (mean)         1.1mm           Deflection under load (individual)         1.2mm           Absorption (Mean)         1.2mm           Absorption (Individual)         2.3%           ≤ 0.8% (width)         0.23%           ≤ 0.4% (length)         0.08%           Absorption (Individual)         2.81%           ≤ 1.2% (width)         0.25%           ≤ 0.6& (length)         0.13%           Mean Absorption -7%         1.18%           Individual Maximum -7%         1.21%           ≤ 7% (mean)         1.42%           Declaration         40%/60% Polymer           1.0% Others           Declaration         74°C           ≤ 50 x 10-6K         2.79 x 10-5mm/mm°C           Declaration         AL *5           Declaration         EN15534-4 P/C W 50 UC3

<sup>\*</sup> Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

### INSTALLATION AND WARRANTY

All Havwoods floors must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent standard worldwide.









The mark of responsible forestry

Havwoods Limited, Carnforth Business Park, Oakwood Way, Carnforth LA5 9FD T.+44(0)1524 737000 F.+44(0)1524 737001 info@havwoods.co.uk www.havwoods.co.uk