



## TECHNICAL DATA SHEET

### HW7834 Istra

#### Design from Havwoods

USAGE: (SEE HAVWOODS QUICK REFERENCE GUIDE TO CHOOSING THE CORRECT FLOOR).



The above image is a finished product and should only be used as a design match.

#### PRODUCT DETAILS

<b>Product Code</b>	HW7834
<b>Product Range</b>	Design from Havwoods
<b>Construction</b>	Engineered
<b>Specie</b>	European Oak
<b>Pattern</b>	Stretched Hexagon
<b>Process</b>	Sanded
<b>Finish</b>	UV Oiled
<b>Profile</b>	Grooved on 3-sides
<b>Edge Profile</b>	Bevelled Edge
<b>Top Layer</b>	4mm European Oak
<b>Backing</b>	Birch Plywood
<b>Thickness</b>	15.5mm (5/8")
<b>Width</b>	140mm (5 1/2")
<b>Length</b>	382mm (15")
<b>Pack Size</b>	0.92m <sup>2</sup> (9.90ft <sup>2</sup> )
<b>Grade</b>	Character
<b>Maintenance</b>	Comprehensive maintenance instructions and materials are available from Havwoods for all floors.

#### INSTALLATION METHODS

<b>Glue Down</b>	Yes* (recommended)
<b>Nailed</b>	No
<b>Floated on underlay</b>	No
<b>Over Underfloor Heating</b>	No

#### GRADING CRITERIA

Typically, character grade will include both heartwood and sapwood and allows a wider range of colour variation. Knots are larger and you should expect checks (cracks across the growth ring). Filler will be used, the colour of which is selected to complement the wood rather than to match it exactly, and it may vary from batch to batch.

N.B. The product grading criteria is inspected at each mill visually and should be taken as an approximation only. Please ask for further details

#### TECHNICAL CRITERIA

<b>Origin</b>	Russia
<b>Responsible Certification</b>	Please ask a member of staff for details
<b>Janka Hardness Rating</b>	1,120 lbf (4,980N)
<b>Formaldehyde Emission</b>	
<b>Slip testing</b>	71/29 PTV (CEN/TS 15676:2007)
<b>Critical Radiant Flux</b>	
<b>Thermal Conductivity</b>	λ 0.13 W/m K (EN 12664)



\* Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

\*\* This product may require on-site sanding prior to applying a suitable finish

# Temperature of top-face must never be allowed to exceed 27°C/80°F. UFH protocol to control temperature conditions is recommended.

‡ Pack lengths will vary between 1950mm or 2400mm dependant upon stock availability.

#### INSTALLATION AND WARRANTY

All Havwoods floors must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors which have been installed by a competent flooring installer comparable to NWFA standards or equivalent standards worldwide.

© This technical data sheet was written by Havwoods International. At the time of writing and publication of the sheet, all information is specified correctly. The company reserves the right to change the specifications of this product at any time without prior notice to third parties. The photographs used in this sheet are intended only as illustrations. No rights can be derived from them.

Havwoods International (North America);  
151 W 18th St, New York, NY 1011, USA  
Tel: 1 844 808 9663 (WOOD)

[Info@havwoodsusa.com](mailto:Info@havwoodsusa.com)

[www.havwoodsusa.com](http://www.havwoodsusa.com)