

TECHNICAL DATA SHEET

HW7964 Istra

Venture Plank

USAGE: (SEE HAVWOODS QUICK REFERENCE GUIDE TO CHOOSING THE CORRECT FLOOR).



PRODUCT DETAILS

Product Code	HW7964	
Product Range	Venture Plank	
Construction	Engineered	
Specie	European Oak (Quercus Robur)	
Pattern	Stretched Hexagon	
Process	Sanded	
Finish	UV Oiled	
Profile	Tongue & Groove	
Edge Profile	Bevelled Edge	
Top Layer	4mm European Oak (Quercus Robur)	
Backing	Birch Plywood (Betula spp.)	
Thickness	15.5mm	
Width	140mm	
Length	382mm	
Pack Size	0.92m²	
Grade	Character	
Maintenance	Comprehensive maintenance instructions and materials are available from Havwoods for all floors.	

INSTALLATION METHODS

Fully Bonded	Yes* (recommended)
Nailed	No
Floated on underlay	No
Over Underfloor Heating	Yes*# (Please ask for our technical guidelines)

GRADING CRITERIA


Typically, character grade will include both heartwood and sapwood and allows a wider range of colour variation. Knots are larger and you should expect checks (cracks across the growth ring). Filler will be use, the colour of which is selected to complement the wood rather than to match it exactly, and it may vary from batch to batch.

N.B. The product grading criteria is inspected at each mill visually and should be taken as an approximation only. Please ask for further details

TECHNICAL CRITERIA

Russia
Please ask a member of staff for details
1,120 lbf (4,980N)
E1(EN 717-1)
< 5ppm (CEN/TR 14823)
71/29 PTV (CEN/TS 15676:2007)
Cfl-s1 (EN 13501-1:2007)
λ 0.13 W/m K (EN 12664)

INSTALLATION AND WARRANTY All Havwoods floor must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent standards worldwide.





^{*} Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

^{**} This product may require on-site sanding prior to applying a suitable finish

[#] Temperature of top-face must never be allowed to exceed 27°C. UFH protocol to control temperature conditions is recomr ‡ Pack lengths will either 1950mm or 2400mm dependant upon stock availability.