

Technical Data Sheet

HW3264 Salvo Venture Plank

Usage: See Havwoods quick reference guide to choosing the correct floor

Installation Methods

Fully Bonded	Yes* (recommended)
Nailed	Yes*
Floated on underlay	Yes*
Over Underfloor Heating	Yes*# (Please ask for our technical guidelines)

Grading Criteria

Typically, prime grade has few, if any knots, and these will be of minimal size. There will also be a minimal amount of sapwood and filler, if any at all. Where filler is used its colour is selected to complement the wood rather than to match it exactly and the colour of the filler may vary from batch to batch. There will be a relatively small amount of colour variation in the timber itself.

N.B. The product grading criteria is inspected at each mill visually and should be taken as an approximation only. Please ask for further details

Technical Criteria

Origin	Europe
Responsible Certification	Please ask a member of staff for details
Janka Hardness Rating	1,120 lbf (4,980N)
Formaldehyde Emission	E1 (EN717-1)
Pentachlorophenol Emission	< 5ppm (CEN/TR 14823)
Slip testing	56/28 PTV (BS7976-2:2002+A1:2013)
Reaction to Fire Certification	Cfl-s1 (EN13501-1)
Thermal Conductivity	λ 0.18 W/m K (EN 12664)

* Please note that this is a smoked/furmed product. This reactive process will typically generate a wider range of colour variation in the product. * Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

** This product may require on-site sanding prior to applying a suitable finish

Temperature of top-face must never be allowed to exceed 27°C. UFH protocol to control temperature conditions is recommended.
Pack lengths will either 1950mm or 2400mm dependant upon stock availability.
Installation and Warranty: All Havwoods floor must be installed by a competent installer who will have the
necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors
which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent
standards worldwide.

This technical data sheet was written by Hawwoods International. At the time of writing and publiciation of the sheet, all information is specified correctly. The company reserves the right to change the specifications of this product at any time without prior notice to third parties. The photographs use in the sheet are intended only as illustrations. No rights can be derived from them.

NS5Plus

Tel: +44 (0)1524 737 000; Fax: +44 (0)1524 737 001 info@havwoods.com www.havwoods.com

Product Details Product Code

Product Code	HW3264
Product Range	Venture Plank
Construction	Multi Layered Engineered
Specie	European Oak (Quercus Robur)
Pattern	Plank
Process	Sanded & Smoked
Finish	UV Oiled
Profile	Tongue & Groove
Edge Profile	2-Sided Bevelled Edge
Top Layer	6mm European Oak (Quercus Robur)
Backing	Birch Plywood (Betula spp.)
Thickness	20mm
Width	180mm
Length	1800-2400mm (May include up to 25% shorter boards)
Pack Size	TBC
Grade	Prime
Maintenance	Comprehensive maintenance instructions and materials are available from Havwoods for all floors.



Version 2.1