

TECHNICAL DATA SHEET

MG14118 Somersby

Magna

USAGE: (SEE HAVWOODS QUICK REFERENCE GUIDE TO CHOOSING THE CORRECT FLOOR).



PRODUCT DETAILS

Product Code	MG14118
Product Range	Magna
Construction	Engineered
Specie	European Oak
Pattern	1-Strip
Process	Brushed & Stained
Finish	Matt Lacquered
Profile	Tongue & Groove
Edge Profile	4-Sided Bevelled Edge
Top Layer	2.5mm European Oak
Backing	Pine Backing
Thickness	14mm (1/2")
Width	180mm (7 1/8")
Length	2200mm (86 5/8")
Pack Size	2.77m ² (29.82ft ²)
Grade	Character
Maintenance	Comprehensive maintenance instructions and materials are available from Havwoods for all floors.

INSTALLATION METHODS

Ensure steel surface on raised access floor is clean from debris and dust to get maximum magnetic bond before laying random planks. Boards can be cut with a cross cutting saw blade, manual or powered.

REMOVAL METHODS

To remove the boards for access, use a suction cup tool. Apply a small amount of washing up liquid to the cup, apply suction cup tool to the surface of the plank to be lifted, next to a joint. Apply pressure whilst you engage the suction cups

GRADING CRITERIA

Typically, character grade will include both heartwood and sapwood and allows a wider range of colour variation. Knots are larger and you should expect checks (cracks across the growth ring). Filler will be used, the colour of which is selected to complement the wood rather than to match it exactly, and it may vary from batch to batch.

N.B. The product grading criteria is inspected at each mill visually and should be taken as an approximation only. Please ask for further details

TECHNICAL CRITERIA

Origin	Europe
Responsible Certification	FSC® Certified (FSC-C009500)
Janka Hardness Rating	1,120 lbf (4,980N)
Formaldehyde Emission	E1 (EN 717-1:2006)
Slip testing	57/28 PTV (CEN/TS 15676:2007)
Critical Radiant Flux	Dfl-s1 (EN 13501-1)
Thermal Conductivity	λ 0.13 W/m K (EN 12664)

MAGNETIC PROPERTIES

Energy (BH Max)	0.6 MGOe
Residual induction Br (Gauss)	600-1800 Gs
Intrinsic coercive force Hci (Osteds)	2405 Oe
Coercive force HcB (Oe)	130

* Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

** This product may require on-site sanding prior to applying a suitable finish

Temperature of top-face must never be allowed to exceed 27°C/80°F. UFH protocol to control temperature conditions is recommended.

INSTALLATION AND WARRANTY

All Havwoods floors must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent standards worldwide.

© This technical data sheet was written by Havwoods International. At the time of writing and publication of the sheet, all information is specified correctly. The company reserves the right to change the specifications of this product at any time without prior notice to third parties. The photographs used in this sheet are intended only as illustrations. No rights can be derived from them.

05-AUGUST-2021/EU