

TECHNICAL DATA SHEET

HW3926 Fortress

Boutique

USAGE: (SEE HAVWOODS QUICK REFERENCE GUIDE TO CHOOSING THE CORRECT FLOOR).



PRODUCT DETAILS

| Product Code | HW3926 | |
|---------------|--|--|
| Product Range | Boutique | |
| Construction | Engineered | |
| Specie | European Oak(Quercus Robur) | |
| Pattern | 1-Strip | |
| Process | Brushed & Smoked^ | |
| Finish | UV Oiled | |
| Profile | Tongue & Groove | |
| Edge Profile | Bevelled Edge | |
| Top Layer | 4.5mm European Oak(Quercus Robur) | |
| Backing | Birch Plywood(Betula spp.) | |
| Thickness | 19mm (3/4") | |
| Width | 180mm (7 1/8") | |
| Length | Random (Random) | |
| Pack Size | 1.30-1.73m2 | |
| Grade | Select | |
| Maintenance | Comprehensive maintenance instructions and materials are available from Havwoods for all floors. | |

[^] Please note that this is a smoked/fumed product. This reactive process will typically generate a wider range of colour variation in the product.

INSTALLATION METHODS

| Fully Bonded | Yes* (recommended) |
|-------------------------|---|
| Nailed | No |
| Floated on underlay | Yes* |
| Over Underfloor Heating | Yes*# (Please ask for our technical guidelines) |

GRADING CRITERIA

Known as either select or classic grade, typically this will have a mix of almost prime boards with other planks which have more knots. Slightly larger knots are allowed in this grade. Heartwood and colour variation in the timber should be expected and there may be some checks (cracks across the growth ring), sapwood and filler. The colour of the filler is intended to complement the natural structure of the wood, where features such as knots are in contrast to the surrounding timber, and it may vary from batch to batch.

TECHNICAL CRITERIA

| Origin | Europe |
|---------------------------|--|
| Responsible Certification | Please ask a member of staff for details |
| Janka Hardness Rating | 1,120 lbf (4,980N) |
| Formaldehyde Emission | BLQ ppm - TSCA VI Compliant |
| Slip testing | 83/24 PTV (CEN/TS 15676:2007) |
| Critical Radiant Flux | Class II - ASTM E 648 |
| Thermal Conductivity | λ 0.17 W/m K (EN 12664) |



^{**} This product may require on-site sanding prior to applying a suitable finish
Temperature of top-face must never be allowed to exceed 27°C. UFH protocol to control temperature conditions is recor ‡ Pack lengths will either 1950mm or 2400mm dependant upon stock availability.

INSTALLATION AND WARRANTY All Havwoods floors must be installed by a competent installer who will have the instruction and warrant in interesting single properties assigned by a competent installed with will have the individual site circumstances into account. Havwoods warrenty will apply only to floors which have been installed by a competent flooring installer comparable to NWFA standards or equivalent standards worldwide.