

Technical Data Sheet

Version 1.0



RECM2075

Venetian Lagoon

Relik



Specification

| | |
|----------------------|---|
| Pattern | Plank |
| Construction | Multi Layered Engineered |
| Top Layer Specie | European Oak (<i>Quercus robur</i>) |
| Surface Process | Smoked [^] |
| Finish | Oiled |
| Connection System | Tongue & Groove |
| Edge Profile | Reclaimed Edge |
| Backing | Eucalyptus Plywood (<i>Eucalyptus grandis</i>) |
| Wear Layer Thickness | 4mm |
| Total Thickness | 19mm |
| Width | 90-270mm |
| Length | 400-3000mm (May include up to 25% shorter boards) |
| Pack Size | Various |
| Grade | Rustic |

Key:

[^] Please note that this is a smoked/ fumed product. This reactive process will typically generate a wider range of colour variation in the product.

** This product may require on-site sanding prior to applying a suitable finish

‡ Pack lengths will vary between the specified minimum and maximum lengths depending upon stock availability.

* Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

Temperature of top-face must never be allowed to exceed 27°C. UFH protocol to control temperature conditions is recommended.

Installation Methods

| | |
|-------------------------|---|
| Fully Bonded | Yes* (recommended) |
| Nailed/Screwed | No |
| Floated on Underlay | Yes* |
| Over Underfloor Heating | Yes*# (Please ask for our technical guidelines) |

All Havwoods floor must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent standards worldwide.

Grading Criteria

| | |
|------------------|-----------------------|
| Sound Knots | Allowed without limit |
| Broken Knots | Up to 50mm Ø allowed |
| Filled Defects | Allowed |
| Heart/Pith | Not allowed |
| Sapwood | Allowed |
| End Checks | Allowed |
| Insect Damage | Not allowed |
| Filler | Allowed |
| Colour Variation | Allowed |
| Small Cracks | Allowed |
| Inner Bark | Allowed |
| Modullary Rays | Allowed |

N.B. The product grading criteria is inspected at each mill visually and should be taken as an approximation only.

Technical Criteria

| | |
|---------------------------------|-------------------------------|
| Origin | Asia |
| Janka Hardness Rating | 1,120 lbf (4,980N) |
| Formaldehyde Emissions | E1 (EN717-1) |
| Pentachlorophenol Emissions | < 5ppm (CEN/TR 14823) |
| Slip Testing | 60/26 PTV (CEN/TS 15676:2007) |
| Reaction to Fire Classification | Dfl-s1 (EN13501-1) |
| Thermal Resistance | 0.18 W/m K (EN 12664) |



HAVWOODS

For More Information Contact Our Experienced Team:

Tel: +44 (0)1524 737 000 | Fax: +44 (0)1524 737 001
Email: info@havwoods.com

Comprehensive maintenance instructions and materials are available from Havwoods for all floors.



This technical data sheet was written by Havwoods International. At the time of writing and publication, all information is specified correctly. The company reserves the right to change the specifications of this product at any time without prior notice to third parties. The photographs used in this document are intended only as illustrations. No rights can be derived from them.

