

TECHNICAL DATA SHEET

HW3190 Willow

Boutique

USAGE: (SEE HAVWOODS QUICK REFERENCE GUIDE TO CHOOSING THE CORRECT FLOOR).



PRODUCT DETAILS

Product Code	HW3190	
Product Range	Boutique	
Construction	Engineered	
Specie	European Oak(Quercus Robur)	
Pattern	35º Plank Chevron	
Process	Brushed	
Finish	Oiled	
Profile	Tongue & Groove	
Edge Profile	4-Sided Bevelled Edge	
Top Layer	3mm European Oak(Quercus Robur)	
Backing	Eucalyptus Plywood(Populus Alba)	
Thickness	15mm (5/8")	
Width	305mm (12")	
Length	1672mm (65 7/8")	
Pack Size	2.04m²	
Grade	Rustic	
Maintenance	Comprehensive maintenance instructions and materials are available from Havwoods for all floors.	

INSTALLATION METHODS

Fully Bonded	Yes* (recommended)
Nailed	No
Floated on underlay	Yes*
Over Underfloor Heating	Yes*# (Please ask for our technical guidelines)

GRADING CRITERIA

Known as either natural or rustic grade this allows a virtually limitless size and number of knots. Heartwood will be used, there will be colour variation, sapwood and filler; you should expect checks (cracks across the growth ring) and possibly some end shake (cracks between the rings). The colour of the filler is intended to complement the natural structure of the wood, where features such as knots are in contrast to the surrounding timber, and it may vary from batch to batch.

oduct grading criteria is inspected at each mill visually and should be taken as an approximation only. Please ask N.B. The pr

TECHNICAL CRITERIA

Origin	China
Responsible Certification	Please ask a member of staff for details
Janka Hardness Rating	1,120 lbf (4,980N)
Formaldehyde Emission	BLQ ppm - TSCA VI Compliant
Slip testing	67/45 PTV (CEN/TS 15676:2007)
Critical Radiant Flux	Class II - ASTM E 648
Thermal Conductivity	λ 0.14 W/m K (EN 12664)





necessary skills and take individual site circumstances into account. Hawwoods warrenty will apply only to floors which have been installed by a competent flooring installer comparable to NWFA standards or equivalent standards worldwide.

^{**} This product may require on-site sanding prior to applying a suitable finish

[#] Temperature of top-face must never be allowed to exceed 27°C. UFH protocol to control temperature conditions is rec

[‡] Pack lengths will either 1950mm or 2400mm dependant upon stock availability.