

Technical Data Sheet

HW8702 Bog Oak Handgrade

Usage: See Havwoods quick reference guide to choosing the correct floor

Installation Methods

Fully Bonded	Yes* (recommended)
Nailed	No
Floated on underlay	No
Over Underfloor Heating	Yes*# (Please ask for our technical guidelines)

Grading Criteria

Typically, prime grade has few, if any knots, and these will be of minimal size. There will also be a minimal amount of sapwood and filler, if any at all. Where filler is used its colour is selected to complement the wood rather than to match it exactly and the colour of the filler may vary from batch to batch. There will be a relatively small amount of colour variation in the timber itself.

N.B. The product grading criteria is inspected at each mill visually and should be taken as an approximation only. Please ask for further details

Technical Criteria

Origin	Europe
Responsible Certification	FSC® Certified (FSC-C009500)
Janka Hardness Rating	1,120 lbf (4,980N)
Formaldehyde Emission	NPD
Slip testing	USRV 104 (CEN/TS 15676:2007-11)
Critical Radiant Flux	NPD
Thermal Conductivity	λ 0.15 W/m K (EN 12667:2001)





The mark of responsible forestry

^ Please note that this is a smoked/fumed product. This reactive process will typically generate a wider range of colour variation in the product. * Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

** This product may require on-site sanding prior to applying a suitable finish

28-MARCH-2024/NA

- # Temperature of top-face must never be allowed to exceed 27°C. UFH protocol to control temperature conditions is recommended.

Fack lengths will either 1950mm of 2400mm dependant upon stock availability. Installation and Warranty: All Havwoods floor must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent standards worldwide.

This technical data sheet was written by Hawwoods International. At the time of writing and publiciation of the sheet, al information is specified correctly. The company reserves the right to change the specifications of this product at any time without prior notice to third parties. The photographs use in the sheet are intended only as illustrations. No rights can be derived from them.



Havwoods International (North America) 151 W 18th St, New York, NY 1011, USA

Tel - 1 347 523 8930 (WOOD) info www.havwoods.com/us

Product Details

Product Code	HW8702
Product Range	Handgrade
Construction	Multi Layered Engineered
Specie	Bog Oak (Quercus Robur)
Pattern	1-Strip
Process	Brushed
Finish	Hardwax Oiled
Profile	Tongue & Groove
Edge Profile	4-Sided Bevelled Edge
Top Layer	5mm Bog Oak (Quercus Robur)
Backing	Birch/Alder Plywood (Betula L.)
Thickness	20mm (3/4")
Width	220-320mm (8 5/8" - 12 5/8")
Length	1500-3000mm (8 5/8" - 12 5/8") (May include up to 25% shorter boards)
Pack Size	TBC
Grade	Prime
Maintenance	Comprehensive maintenance instructions and materials are available from Havwoods for all floors.

Version 2