

Technical Data Sheet

HW8722 Bog Oak Handgrade

Usage: See Havwoods quick reference guide to choosing the correct floor

Installation Methods

| Fully Bonded | Yes* (recommended) |
|-------------------------|---|
| Nailed | No |
| Floated on underlay | No |
| Over Underfloor Heating | Yes*# (Please ask for our technical guidelines) |

Grading Criteria

Typically, prime grade has few, if any knots, and these will be of minimal size. There will also be a minimal amount of sapwood and filler, if any at all. Where filler is used its colour is selected to complement the wood rather than to match it exactly and the colour of the filler may vary from batch to batch. There will be a relatively small amount of colour variation in the timber itself.

N.B. The product grading criteria is inspected at each mill visually and should be taken as an approximation only. Please ask for further details

Technical Criteria

| Origin | Europe |
|---------------------------|------------------------------|
| Responsible Certification | FSC® Certified (FSC-C009500) |
| Janka Hardness Rating | 1,120 lbf (4,980N) |
| Formaldehyde Emission | NPD |
| Slip testing | NPD |
| Critical Radiant Flux | NPD |
| Thermal Conductivity | NPD |





The mark of responsible forestry

* Please note that this is a smoked/fumed product. This reactive process will typically generate a wider range of colour variation in the product.
* Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

** This product may require on-site sanding prior to applying a suitable finish

Temperature of top-face must never be allowed to exceed 27°C. UFH protocol to control temperature conditions is recommended. ‡ Pack lengths will either 1950mm or 2400mm dependant upon stock availability.

Installation and Warranty: All Havwoods floor must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent standards worldwide.

This technical data sheet was written by Hawwoods International. At the time of writing and publciation of the sheet, all information is specified correctly. The company reserves the right to change the specifications of this product at any time without prior notice to third parties. The photographs use in the sheet are intended only as illustrations. No rights can be derived from them.



Havwoods International (North America) 151 W 18th St, New York, NY 1011, USA

Tel - 1 347 523 8930 (WOOD) info@havwoodsusa.com www.havwoods.com/us

Product Details

| Product Code | HW8722 |
|---------------|---|
| Product Range | Handgrade |
| Construction | Multi Layered Engineered |
| Specie | Bog Oak (Quercus Robur) |
| Pattern | Herringbone |
| Process | Brushed |
| Finish | Hardwax Oiled |
| Profile | Tongue & Groove |
| Edge Profile | 4-Sided Bevelled Edge |
| Top Layer | 5mm Bog Oak (Quercus Robur) |
| Backing | Birch/Alder Plywood (Betula L.) |
| Thickness | 20mm (3/4") |
| Width | 90mm (3 1/2") |
| Length | 540mm (3 1/2") |
| Pack Size | TBC |
| Grade | Prime |
| Maintenance | Comprehensive maintenance instructions and materials are available from Havwoods for all floors. |
| | |