



Technical Data Sheet

Version 1.1

HW3813

Medio

V Cycle



Specification

Pattern	Plank
Construction	Multi-Layered Engineered
Top Layer Specie	European Oak (Quercus robur)
Surface Process	Sanded & Smoked
Finish	Natural Oiled
Connection System	Tongue & Grooved
Edge Profile	2-Sided Bevelled Edge
Backing	Birch Plywood (Betula spp.)
Wear Layer Thickness	3.5mm
Total Thickness	12.7mm
Width	180mm
Length	1950-2400mm (May include up to 25% shorter boards)
Pack Size	TBC
Grade	Rustic



The mark of
responsible forestry

Key:

^ Please note that this is a smoked/fumed product. This reactive process will typically generate a wider range of colour variation in the product.

* Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

Temperature of top-face must never be allowed to exceed 27°C. UFH protocol to control temperature conditions is recommended.

Installation Methods

Fully Bonded	Yes* (recommended)
Nailed/Screwed	No
Floated on Underlay	Yes*
Over Underfloor Heating	Yes*# (Please ask for our technical guidelines)

All Havwoods floor must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent standards worldwide.

Grading Criteria

Sound Knots	Up to 80mm Ø allowed
Broken Knots	Up to 60mm Ø allowed
Filled Defects	Allowed
Heart /Pith	Allowed
Sapwood	Not Allowed
End Checks	Allowed, 400mm x 8mm
Insect damage	Not Allowed
Filler	Allowed
Colour variation	Allowed
Small cracks	Allowed, 1200mm x 2mm
Inner bark	Allowed, 50mm x 3mm
Modullary Rays	Allowed

N.B. The product grading criteria is inspected at each mill visually and should be taken as an approximation only. To allow for unavoidable variations in the material characteristics, 3% of materials may vary from the stated range.

Technical Criteria

Origin	Europe
Certification	FSC® Certified (FSC-C009500)
Janka Hardness Rating	1,120 lbf (4,980N)
Formaldehyde Emissions	E1 (EN 717-1)
Pentachlorophenol Emissions	< 5ppm (CEN/TR 14823)
Slip Testing	78/58 PTV (CEN/TS 15676:2007)
Reaction to Fire Classification	Cfl-s1 (EN 13501-1:2007)
Thermal Conductivity	0.17 W/m K (EN 12664)



HAVWOODS

For More Information Contact Our Experienced Team:

Tel: +44 (0)1524 737 000 | Fax: +44 (0)1524 737 001
Email: info@havwoods.com

Comprehensive maintenance instructions and materials are available from Havwoods for all floors.



This technical data sheet was written by Havwoods International. At the time of writing and publication, all information is specified correctly. The company reserves the right to change the specifications of this product at any time without prior notice to third parties. The photographs used in this document are intended only as illustrations. No rights can be derived from them.

