




Technical Data Sheet

Version 1.0

HW6574

Walnut Parisienne

Venture Plank



Specification

Pattern	Mansion Weave
Construction	Multi-Layered Engineered
Top Layer Specie	American Black Walnut (<i>Juglans nigra</i>)
Surface Process	Sanded
Finish	Lacquered
Connection System	Tongue & Groove
Edge Profile	Bevelled Edge
Backing	Birch Plywood (<i>Betula</i> spp.)
Wear Layer Thickness	3.5mm
Total Thickness	18mm
Width	198/140mm
Length	594/560mm
Pack Size	TBC
Grade	Select

Key:

* Subject to compatible subfloor and correct installation (see Installation Guidelines) including sensors.

Temperature of top-face must never be allowed to exceed 27°C. UFH protocol to control temperature conditions is recommended.

Installation Methods

Fully Bonded	Yes* (recommended)
Nailed/Screwed	No
Floated on Underlay	No
Over Underfloor Heating	Yes*# (Please ask for our technical guidelines)

All Havwoods floor must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Havwoods warranty will apply only to floors which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent standards worldwide.

Grading Criteria

Sound Knots	Up to 5mm Ø allowed
Broken Knots	Up to 5mm Ø allowed
Filled Defects	Allowed
Heart /Pith	Not allowed
Sapwood	Up to 25% of the width
End Checks	Not allowed
Insect damage	Not allowed
Filler	Allowed
Colour variation	Allowed
Small cracks	Not allowed
Inner bark	Not allowed
Modullary Rays	Allowed

N.B. The product grading criteria is inspected at each mill visually and should be taken as an approximation only. To allow for unavoidable variations in the material characteristics, 3% of materials may vary from the stated range.

Technical Criteria

Origin	Europe
Janka Hardness Rating	1,010 lbf (4,490 N)
Formaldehyde Emissions	E1 (EN 717-1)
Pentachlorophenol Emissions	< 5ppm (CEN/TR 14823)
Slip Testing	USRV 56 (CEN/TS 15676:2007-11)
Reaction to Fire Classification	Cfl-s1 (EN 13501-1:2018-12)
Thermal Conductivity	0.14 W/m K (EN 12664:2001)



HAVWOODS

For More Information Contact Our Experienced Team:

Tel: +44 (0)1524 737 000 | Fax: +44 (0)1524 737 001
Email: info@havwoods.com

Comprehensive maintenance instructions and materials are available from Havwoods for all floors.



This technical data sheet was written by Havwoods International. At the time of writing and publication, all information is specified correctly. The company reserves the right to change the specifications of this product at any time without prior notice to third parties. The photographs used in this document are intended only as illustrations. No rights can be derived from them.

