

UL Approved FIRE-RATED PANEL

arauco
Fire-Rated **DURAFLAKE**

www.arauco-na.com

SPECIFICATION SHEET

DURAFLAKE Fire-Rated* is a UL approved Class A/Class 1 fire-rated particleboard panel. This nationally recognized fire-rated panel is classified by Underwriters Laboratories for surface burning characteristics using the UL 723 Test Method. Panels are retardant throughout, stay classified after cutting and have a wide range of sizes available.

*Fire-Rated products manufactured in Albany, OR are available in widths up to 5 ft. and products manufactured in St. Stephen, NB are available in widths up to 4 ft.

DURAFLAKE FIRE-RATED

		Albany, OR		
Thickness Range	(in./mm)	3/8" - 15mm	5/8" - 3/4"	13/16" - 1 1/2"
Average MOR	(psi)	1,600	1,600	1,600
Average MOE	(psi)	325,000	325,000	300,000
Average Internal Bond	(psi)	75	75	60
Face Screw Hold	(lb)	240	240	240
Edge Screw Hold	(lb)	N/A	190	175
Thickness Tolerance	(in.)	+/- .005	+/- .005	+/- .005
Linear Expansion	%	0.40	0.40	0.35
Length and Width	(in.)	+/- 1/16	+/- 1/16	+/- 1/16
Square	(in.)	+/- 1/8	+/- 1/8	+/- 1/8

- The above physical properties are based on minimum allowable averages of individual production lots. Testing for conformance to the above specifications must be done in accordance with procedures described in the American National Standard for Particleboard (ANSI 208.1 - 2016 section 6.2 Sampling for Acceptance)
- EPA recognized and CARB approved Third Party Certifier TPC-1
- EPA TSCA Title VI certified. Complies with CARB ATCM 93120, ANSI 208.1 ANSI 208.1 - 2016, HUD 24 CFR, CAN/CSA - 0160 - 16 for formaldehyde emissions.
- All panels are approved for interior, non-structural application.
- Contains Recycled/Recovered wood content.

Applicable Standard Tests

- ASTM E 84 Standard Test for Surface Burning Characteristics of Building Materials.
- ASTM C 236 Guarded Hot Box Test.
- UL 723 Test for Surface Burning Characteristics of Building Materials.
- CAN/ULC - S102 Test for Surface Burning Characteristics of Building Materials.

Usage Notes:

Some laminates applied to DURAFLAKE® FR or VESTA FR particleboard may change the flame spread rating. Standard available woodworking glues have been successfully used in lamination. However, some adhesives may have compatibility problems with the chemical system used to manufacture DURAFLAKE® FR or VESTA FR particleboard. Any adhesive should be tested for compatibility with the chemical system in DURAFLAKE® FR or VESTA FR particleboard prior to full-scale gluing. Questions should be directed to the glue supplier. When using DURAFLAKE® FR or VESTA FR particleboard in wall systems, an integral vapor barrier must be a properly installed component of the wall in any of the following conditions: the wall has an exterior side and the wall separates spaces conditioned unequally. Joints between panels to be designed to accommodate movement of up to .40 percent. Splined or articulated joints for reveals per AWI Section 500, 500A-G-4 "Joints and Transitions" or similar is suggested. Wood veneers and other laminates should be tested for compatibility with DURAFLAKE® FR or VESTA FR particleboard prior to use. Some wood veneers, laminates, and other types of products may have reactions to surface coatings and finishes, glues, pressing temperatures, moisture, contaminants, the chemical systems used to manufacture FR particleboard products, the failure to use UV inhibitors, or due to other causes. Reactions may include discoloration to veneer or laminate. ARAUCO is not responsible for discoloration or for claims associated with discoloration. Please contact your Sales Representative for more information.

Building Codes

- ICC – International Code Council – 2009 International Fire Code.
- NFPA – National Fire Protection Association - NFPA 101 Life Safety Code - NFPA 5000 Building Construction Safety Code.

Storage and Handling

Particleboard products made by ARAUCO should never be stored or used outdoors. The indoor storage area should be clean, dry, well ventilated, and free of dust, dirt or particles that could contaminate the particleboard. Store flat on stickers on a level, hard, dry surface. Constant relative humidity and temperature should be maintained. Before use, allow to stabilize to the same conditions as are expected after the panel is installed. Condition 48 to 72 hours prior to lamination. For more information, see Composite Panels Association Technical Bulletin: Storage and Handling of Particleboard and MDF.

Safety Data Sheets available online.

renewables
for a
better life

arauco

