

BULK CONTACT ADHESIVE PRODUCT DESCRIPTION



	Description	Colors Available	Solids	Viscosity (cps)	Density (Wt/gl)	Flammable	SCAQMD/ OTC Compliant	Open Time (min)	Postform Grade	VOC (g/L)	Coverage Per Gallon (sq. ft.) (Bonded Surface)
Brush											
HY-70 HY-80	Standard Brush Premium Brush	Natural	20%	1000	6.8	Yes	No No	60	Yes	602	152
HY-80 PLUS	Consumer Grade	Natural	21%	2000	7.2	Yes	No No	45	Yes	684	145
B680H	Low VOC Brush / Spray	Natural	42%	600	7.6	Yes	No Yes	30	No	217	200
HY-80NFM	Non-Flam Brush Grade	Natural	14%	900	10.7	No	No Yes	30	No	240	110
Spray											
	Premium	Red Natural	18%	125	6.7	Yes	No No	60	Yes	588	145
HY-12R HY-12	Premium	Red Natural	19%	175	6.6	Yes	No No	60	Yes	593	145
HY-36R HY-36	Low Solids Economy	Red Natural	17%	200	6.6	Yes	No No	30-45	No	578	133
HY-36MR HY-36M	Low Solids Economy	Red Natural	17%	210	7.0	Yes	No No	30-45	No	576	133
HY-HS+ HY-HSR+	High Solids	Natural Red	24%	135	6.8	Yes	No No	30	Yes	546	185
HY-B60 HY-B60R	General Purpose	Natural Red	28%	140	6.5	Yes	No No	60	No	507	165
HY-B68 HY-B68R	High Solids Low VOC	Natural Red	37%	140	7.5	Yes	No Yes	60	No	241	275
HY-88 HY-88R	OTC & CAL Compliant	Natural Red	37%	200	8.0	Yes	Yes Yes	30	No	0	275
HY-12NFM HY-12NFR	Non-Flam Spray Grade	Natural Red	10.5%	200-250	10.7	No	No Yes	30	Yes	249	95
HY-75NFMG HY-75NFM	High Solids Non-Flam Spray Grade	Green Natural	27%	350	10.1	No	No Yes	30	No	0	225
HY-B68NF HY-B68NFG	High Solids OTC	Natural Green	26%	90	10.0	No	No Yes	30	No	0	225
HY-575 HY-575R	High Solids n-propyl Bromide	Natural Red	27%	350	10.2	No	No No	30	No	885	275
CBA-2501	High Solids Non-Flam, Non-nPb, Non-MeCl	Natural	38%	1500	10.36	No	Yes Yes	30	No	765	325
Water Base											
HY-30 HY-30G	Traditional Water base	Natural Green	56%	1100	9.2	No	Yes Yes	60	Yes	0	400
HY-31# HY-31#G	Neoprene Water base	Natural Green	54%	600	9.2	No	Yes Yes	60	Yes	53	375

BULK CONTACT OFFSETS



	Characteristic	Sta-Put (TACC)	Helmitin	Wilson Art	Premier Bond (Northstar)	StarStuck (Northstar)	Fastbond (3M)	Weldwood (DAP)	Tensor Grip	Nevamar	Pionite	Everstrong	Quality Aerosol
Brush													
HY-70	Standard Brush	S140	4530		PB941+	SS 35+	10	2056	LB28	N/A	N/A	ES300	N/A
HY-80	Premium Brush	2153	4535	500	PB950+			308					
HY-80 PLUS	Consumer Grade	S145	N/A	600	PB935	NS55	N/A	2090	N/A	N/A	N/A	N/A	N/A
B680H	Low VOC	N/A	N/A	1730/1731	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
HY-80NFM	Non-Flam Brush Grade	N/A	4505	N/A	PB955	NS 55	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Spray													
	Premium	S150 S151	4545	800/801 844	PB938	SS38	1357-L	N/A	N/A	NV900	PT9	N/A	N/A
HY-12R	Premium	S155 S156	4560	800/801 860/861	PB938 940	SS38 SS40	N/A	0306/0307	LB25	NV900	PT9	ES900	N/A
HY-36R	Low Solids Economy	S158 S159 773-40	4540	950 951	N/A	N/A	N/A	Rely-on	N/A	NV700	PT7	ES700	N/A
HY-36MR	Low Solids Economy	S158 S159 773-40	4540	950 951	N/A	N/A	N/A	Rely-on	N/A	NV700	PT7	ES700	N/A
HY-HS+	High Solids	2621T	4570	810/811	N/A	N/A	1357	1145	N/A	N/A	N/A	N/A	N/A
HY-B60	General Purpose												
HY-B68	High Solids Low VOC	SP80	1570	1700/1701 1730/1731	PB912	N/A	N/A	N/A	N/A	N/A	N/A	N/A	Q8005 Q5250
HY-88	OTC & CAL Compliant	SP80	1570	1700/1701 1730/1731	PB910	HL+	94CA	N/A	N/A	N/A	N/A	ES80 ES10	Q8005 Q8550
HY-12NFM	Non-Flam Spray Grade	S120M	4510	N/A	PB970	NS 70	N/A	2004 2044	LB29	N/A	N/A	N/A	N/A
HY-75NFMG	High Solids Non-Flam Spray Grade	S170	1585	N/A	PB975	NS 75	N/A	2146	LB10N	N/A	N/A	ES800*	N/A
HY-B68NF	High Solids OTC	S170	1585	N/A	PB975	NS 75	98NF	2146	LB10N	N/A	N/A	ES800*	N/A
HY-575	High Solids n-propyl Bromide	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
HY-575R	High Solids Non-Flam, Non-nPb, Non-MeCl	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
CBA-2501													
Water Base													
HY-30	Traditional Water base	S160 S162	776 8320-6	H20	PB2008	SS2008	30	3030	N/A	NV11	PT11	ESW10 ESW11	Q5550
HY-31	Neoprene Water base	S160 S162	776 8320-6	H20	PB2008	SS2008	30	3030	N/A	NV11	PT11	ESW10 ESW11	Q5550
Wood Glue													
HY-GG	Yellow Wood Glue		856	20				Original Wood Glue	N/A	NV1Y	PT1Y	ESYG	Q2000/Q2001
XA-2600	White Wood Glue		842	10					N/A	NV1W	PT1W	ESWG	Q2000/Q2001