Medite[®]Lite

MEDFORD, OR

TECHNICAL DATA	IMPERIAL	METRIC
Widths	4 & 5 ft	1.22 & 1.52 m
Lengths	up to 18 ft	up to 5.49 m
Thicknesses	1/2 – 1 in	12.7 – 25.4 mm
Density	42 lbs/ft ³	673 kg/m ³
Internal Bond	115 psi	0.79 Nmm ²
Modulus of Rupture/MOR	3,000 psi	20.7 Nmm ²
Modulus of Elasticity/MOE	325,000 psi	2,241 Nmm ²
Hardness/MOH	900 lbs	4,003 N
Screw Holding – Face	180 lbs	800 N
Screw Holding – Edge	150 lbs	667 N
Thickness Swell	5.5%	
Linear Expansion	0.30%	
Moisture Content	4 - 6%	
Flame Spread Rating	Class C (3)	
Dimensional Tolerances:		
Length/Width Squareness Thickness – panel average from specified	±0.080 in ±0.036 in/ft ±0.005 in	±2.0 mm ±3.0 mm/m ±0.125 mm
Thickness – variance from panel average	±0.005 in	±0.125 mm

MEDIUM DENSITY FIBERBOARD

Lightweight, economy-grade medium density fiberboard (MDF).

COMMON APPLICATIONS

- Hook and cleat for closets and shelving
- Wall cladding/wainscot
- Standing and running trim

Values represent averages for 3/4" panels. Mechanical properties are tested in accordance with ASTM D1037.

Customer-specified grades are available by request and subject to minimum order quantities.

Medite[®]Lite

MEDFORD, OR



GREEN BUILDING SUPPORT:

For LEED® and other green building support documentation, visit roseburg.com/product/medite-lite