Medite[®]

MEDFORD, OR

TECHNICAL DATA	IMPERIAL	METRIC
Widths	4 & 5 ft	1.22 & 1.52 m
Lengths	up to 18 ft	up to 5.49 m
Thicknesses	1/4 – 1-1/2 in	6.35 – 38.1 mm
Density	47 lbs/ft ³	753 kg/m ³
Internal Bond	160 psi	1.10 Nmm ²
Modulus of Rupture/MOR	3,800 psi	26.2 Nmm ²
Modulus of Elasticity/MOE	420,000 psi	2,896 Nmm ²
Hardness/MOH	1,000 lbs	4,448 N
Screw Holding – Face	225 lbs	1,001 N
Screw Holding – Edge	200 lbs	890 N
Thickness Swell	5.0%	
Linear Expansion	0.30%	
Moisture Content	4 - 6%	
Flame Spread Rating	Class C (3)	
Dimensional Tolerances:		
Length/Width Squareness Thickness – panel average from specified Thickness – variance from panel average	±0.080 in ±0.036 in/ft ±0.005 in	±2.0 mm ±3.0 mm/m ±0.125 mm
Thickness – variance from panel average	±0.005 in	±0.125 mm

MEDIUM DENSITY FIBERBOARD

Standard industrial-grade MDF.

COMMON APPLICATIONS

- Cabinetry
- Furniture
- Retail displays
- General lamination (TFL, veneer)
- Wall cladding
- Store fixtures

Values represent averages for 3/4" thick panels. Mechanical properties are tested in accordance with ASTM D1037.

Customer-specified grades are available by request and subject to minimum order quantities.

Medite[®]

MEDFORD, OR



GREEN BUILDING SUPPORT:

For LEED® and other green building support documentation, visit roseburg.com/product/medite