



# Collins Pine Particleboard

- High pine content
- CARB Exempt
- EPA TSCA Title VI Compliant
- 100% post-industrial recycled/recovered content
- Moisture resistant
- NAF-no added formaldehyde



- Commercial
- Industrial
- IND 2
- IND 3







# Collins Pine Particleboard

CollinsWood.com

Mosquito Ridge in the FSC®-certified **Collins Almanor Forest**, tucked into the Sierra Nevada mountains of northern California. It has been logged five times in the last fifty years, yet because of sustainable practices is still a biodiverse, multi-layered forest of mixed age and species. Timberlands acquired in 1902 have been managed on an uneven-age, sustained yield basis from the beginning. In 1993, it was the first Collins forest to become certified. Species include Ponderosa Pine, White Fir, and Sugar Pine.



## Exceptionally high percentage of western pine fiber

- **Excellent machinability**
- **Extends tool life, which increases productivity and reduces costs**
- **Light tan color allows for the use of thin and light papers and melamines**
- **Color, surface, and core qualities are consistent from panel-to-panel**

## Guaranteed smooth—every board, every time

- **Remarkably smooth surface for all laminating applications**
- **Panels are sawn after sanding, eliminating thin edges**
- **Our cross-panel sanding process gives you the smoothest panel in the industry**
- **Increases your production with higher yields**



SCS Validation  
SCS-NAF-04354

Sizes/Thicknesses	Commercial Specifications	Industrial Specifications
Press Size	5' x 24'	5' x 24'
Thickness (Inches)*	5/8" – 1"	3/8" – 1-3/16"
Thickness Tolerance**	±.003" avg thickness from target range**	±.003" avg thickness from target range
Length/Width Tolerances	±1/16"	±1/16"
Squareness Tolerance	±1/32" per foot of panel width	±1/32" per foot of panel width

\*Metric sizes within range also available \*\*Based on 3/4"

Physical Properties*	Commercial Specifications	Industrial Specifications	IND 2	IND 3
Density	42 lbs/cu ft	45 lbs/cu ft	46 lbs/cu ft	47 lbs/cu ft
Internal Bond	60 psi	80 psi	90 psi	100 psi
Modulus of Rupture	1310 psi	1700 psi	1885 psi	2176 psi
Modulus of Elasticity	257,000 psi	298,000 psi	290,100 psi	362,600 psi
Screw Holding – Face	171 lbs	205 lbs	225 lbs	225 lbs
Screw Holding – Edge	108 lbs	155 lbs	180 lbs	202 lbs

\*Physical properties tested using method ASTM D 1037-06a. Complies with ANSI A208.1-2016.

## INFORMATION & SALES

### Lee Jimerson

ljimerson@collinsco.com  
503.826.5266

### Mike Shuey

mshuey@collinsco.com  
503.826.5222

Toll Free: 800.547.1793

## COLLINSWOOD® FSC

Made in Klamath Falls, Oregon USA

- **Hardwood Lumber**
- **Softwood Lumber**
- **Collins Pine FreeForm®**
- **Collins Pine FreeForm MR50®**
- **TruWood® Siding | Trim**

 100% Recycled/50% Post Consumer/Processed Chlorine Free 04.21



Since 1855