



MODIFIED LUMBER

INFORMATION SHEET

Product overview

Modified Lumber delivers beauty and high performance in one product. It starts out life as a softwood plantations and its unique modification process to deliver wood whose greatly improved properties and appearance match or exceed tropical species. It is suitable for decking, flooring, interior wall paneling, cladding and general millwork including doors and windows.

Modified Lumber is supplied as rough sawn random grain four-sides clear, and is available in the following dimensions:

Thickness	Widths	Lengths
4/4 (25mm)	6" (150mm)	6'11" - 19'8"
5/4 (32mm)	8" (200mm)	(2.1m - 6m)
6/4 (38mm*)		
8/4 (50mm*)		
Quartersawn Deckboards		
4/4 (25mm)	4" (100mm)	6'11" - 15'7"
	5" (125mm)	(2.1m - 4.8m)
	6" (150mm)	

*Available in second half of 2021

Machining

Using machine settings for medium density hardwoods such as Teak and Red Oak, an excellent finish can be achieved through planing. The quality of finish means no further sanding is necessary prior to coating is PH neutral and, as a result, does not react with coatings, giving good coatings performance as tested by leading brands.

Any stick indentation and underlying stick marks can usually be removed through planing off the surface.

Modified Lumber Properties

Durability: Against decay fungi - European Durability Class 1 Very Durable (EN 113)

Durability against termites: Tested using AWPA E1-17. On a rating of 0-10 where 10 is not attacked, modified timber scored 9.5.

Summary of ASTM D143 test results:

Janka Hardness - 1574lbf
 MOR (psi) - Bending Strength 12,152 psi
 MOE (psi) - Bending Stiffness 1,746,840 psi

Average density: 650kg/m3 (41 lbs./ft3 similar to Teak or Red Oak)

Dimensionally stable: Small movement (BRE Digest No 34 method). Average tangential change in dimension of 1.22% and average radial change of 0.8% when first conditioned at 90% RH at 20°C followed by conditioning at 60% RH at 20°C.

VISUAL GRADE

The following may be present:

Small Knots

5mm or less (no limit on numbers).

Resin pockets

10mm wide, 50mm long totally encased within timber (less than 50mm board thickness) and 10mm wide, 100mm long totally encased within timber (board thickness greater than 50mm).

Intergrown knot

Tight and totally encased maximum 15mm (in board thickness greater than 50mm only).

Resin streaks

Three, maximum width 7mm, 100mm in length.

Surface checking

At the time of delivery, surface checking may be evident at certain times of the year

End splits

Not to exceed 150mm in length.

Distortion

See the distortion tables in our "Visual Grade Specification 2019" brochure.

Wane

Up to 1/4 of board length, 8mm x 8mm for 25mm-50mm thick boards, up to 1/2 of board length, 10mm x 10mm for boards greater than 50mm in thickness.

Kiln-dried with minimal visual defects, random grained (flat sawn).

Proudly distributed by

HARDWOODS

Materials That Inspire

Canada: 844-365-6995 | USA: 888-826-5528
www.hardwoods-inc.com

Specification support by

Design one Source
 Where Inspiration and Design Meet Supply

866-599-1433 | www.designonesource.com