



## CARB Compliant Echo Wood Veneers

Based on the ASTM D6007 North American Small Chamber Test Method the following are test results for Echo Wood veneers.

Echo Wood veneer	Concentration (ppm)	CARB Phase II Emission Ceiling
African Wenge TD-5843S	0.019	0.050 ppm
Champagne Champ-2Q	0.022	0.050 ppm
Qrt Cherry CH-311S	0.038	0.050 ppm
Qrt Ebony EB-7001S	0.021	0.050 ppm
VG Fir Fir-3Q	0.029	0.050 ppm
Qrt Gun Metal Ebony WT-2450S	0.016	0.050 ppm
Qrt Maple MP-016S	0.019	0.050 ppm
Rift W. Oak Oak-12-1S	0.013	0.050 ppm
F/C Rosewood RW-3350C	0.021	0.050 ppm
Sandstone HM-2Q	0.023	0.050 ppm
Slate BA-03S	0.015	0.050 ppm
Qrt Teak TK-016S	0.024	0.050 ppm
F/C Walnut WT-3160C	0.014	0.050 ppm
Qrt Walnut WT-139S	0.028	0.050 ppm
Qrt Wenge WG-111Q	0.014	0.05 ppm
Qrt Zebrano ZB-011S	0.016	0.050 ppm

For additional information visit our website at:

[www.hardwoods-inc.com](http://www.hardwoods-inc.com)

or contact Rich Gorrill at [rgorrill@hardwoods-inc.com](mailto:rgorrill@hardwoods-inc.com)