

# NP511

## TECHNICAL DATA BULLETIN

GRADE: NP511

NEMA: G-11

U.L. LISTED: Y<sup>2</sup>

DESCRIPTION: NP511 consists of a woven glass fabric combined with high temperature epoxy resin system. NP511 has excellent mechanical strength and electrical properties from cryogenic to elevated temperatures. This material meets NEMA G-11 and MIL-I-24768/3, Type GEB and IEC-60893-3-2 EP GC 203.

### TYPICAL PROPERTIES

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
<b>PHYSICAL PROPERTIES</b>					
<b>Specific Gravity</b> (ASTM D792)		-			1.80
<b>Rockwell Hardness</b> (ASTM D785)	0.250" Build-up	M Scale	112		
<b>Moisture Absorption</b> (ASTM D570)	Condition A	%	0.20		
<b>Flexural Strength</b> (ASTM D790)	Condition A	psi (MPa)	68,100 / 61,300 (469.5) / (422.6)		
	LW / CW				
	Condition E-1/150: T-150	psi (MPa)	40,000 / (275.8) /		
	LW / CW				
<b>Flexural Modulus</b> (ASTM D790)	Condition A	kpsi (GPa)	3,000 / 2,700 (20.7) / (18.6)		
	LW / CW				
<b>Tensile Strength</b> (ASTM D638)	Condition A	psi (MPa)	43,000 / 37,000 (296.5) / (255.1)		
	LW / CW				
<b>Izod Impact Strength</b> (ASTM D256)	Condition A	ft-lb/in (J/cm)			
	LW / CW				
	Condition E-48/50	ft-lb/in (J/cm)	12.00 / 9.00 (6.41) / (4.80)		
<b>Compressive Strength</b> (ASTM D695)	Condition A	psi (MPa)	72,500 (499.9)		
	Flatwise				
<b>Bonding Strength</b> (ASTM D229)	Condition A	lb (kg)	1,900 (861.8)		
<b>Shear Strength</b> (ASTM D732)	Condition A	psi (MPa)	22,000 (151.7)		
	Perpendicular				

# TECHNICAL DATA BULLETIN

GRADE: NP511

NEMA: G-11

U.L. LISTED: Y <sup>2</sup>

## TYPICAL PROPERTIES (continued)

	UNITS	VALUE		
		Thickness Tested		
		0.0625"	0.125"	0.500"
<b>THERMAL PROPERTIES</b>				
<b>Temperature Index</b> <sup>1</sup> (UL Bulletin 746b) Electrical / Mechanical	°C	170 / 180		
<b>Coefficient of Thermal Expansion</b> (IPC-TM 650-2.4.24) X-axis / Y-axis	" / °C x10 <sup>-6</sup>		13.0 / 15.0	
<b>Tg by DMA</b>	°C			180
<b>Flammability Rating</b> Condition A (UL Bulletin 94)	Class	HB		
<b>ELECTRICAL PROPERTIES</b>				
<b>Dissipation Factor @ 1 MHz</b> (ASTM D150) Condition A	-			
	Condition D-24/23	-	0.020	
<b>Relative Permittivity @ 1 MHz</b> (ASTM D150) Condition A	-			
	Condition D-24/23	-	4.80	
<b>Breakdown Voltage</b> (ASTM D149) Condition A	kVolts	60		
	Condition D-48/50	kVolts	55	
<b>Electric Strength</b> (ASTM D149) Condition A	Volts/mil (kV/cm)	700 (275.6)		
	Condition D-48/50	Volts/mil (kV/cm)	720 (283.5)	
<b>Arc Resistance</b> (ASTM D495) Condition A	sec		120	
<b>Comparative Tracking Index</b> (ASTM D3638)	Volts		150	

<sup>1</sup> This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

<sup>2</sup> Only applies to thicknesses greater than 0.024".

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.



# TECHNICAL DATA BULLETIN

**GRADE: NP511**

**NEMA: G-11**

**U.L. LISTED: Y <sup>2</sup>**

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, [www.norplex-micarta.com](http://www.norplex-micarta.com), to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.