

MC223 TECHNICAL DATA BULLETIN

GRADE: MC223 U.L. LISTED: N

DESCRIPTION: Grade MC223 is a medium weave cotton phenolic composite. Typical applications include pintle and stave-type bearings for rudder shafts in the marine industry. This material is known industry wide as "Marine Micarta." This product is also suitable for heavy equipment applications that require finer machining profiles than those provided by bearing-grade laminates.

TYPICAL PROPERTIES

				VALUE		
		UNITS	Thickness Tested			
				0.125"	0.500"	
PHYSICAL PROPERTIES						
Specific Gravity						
(ASTM D792)			-		1.44	
Rockwell Hardness						
(ASTM D785)	0.250" Build-up		M Scale		105	
Moisture Absorption	Condition A					
(ASTM D570)			%	1.20		
Flexural Strength	Condition A		psi	18,000 /		
(ASTM D790)	L\	W / CW	(Mpa)	(124.1) /		
Tensile Strength	Condition A		psi	12,000 /		
(ASTM D638)	L\	W / CW	(Mpa)	(82.7) /		
Izod Impact Strength	Condition A		ft-lb/in			
(ASTM D256)	L\	W / CW	(J/cm)			
	Condition E-48/50		ft-lb/in		2.00 / 1.20	
	L\	W / CW	(J/cm)		(1.07) / (0.64)	
Compressive Strength	Condition A		psi	38,000		
(ASTM D695)	F	Flatwise	(Mpa)	(262.0)		
Bonding Strength	Condition A		lb		1,700	
(ASTM D229)			(kg)		(771.1)	
Shear Strength	Condition A		psi	13,000		
(ASTM D732)	Perper	ndicular	(Mpa)	(89.6)		



TECHNICAL DATA BULLETIN

GRADE: MC223 U.L. LISTED: N

TYPICAL PROPERTIES (continued)

		LINITO	VALUE		
		UNITS	Thickness Tested		
			0.125"	0.500"	
THERMAL PROPERTIES					
Temperature Index ¹ (UL Bulletin 746b)	Electrical / Mechanical	°C		/ 125	
Flammability Rating	Condition A				
(UL Bulletin 94)		Class	HB		

¹ This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, www.norplex-micarta.com, to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.