

NP630

TECHNICAL DATA BULLETIN

GRADE: NP630

U.L. LISTED: N

DESCRIPTION: NP630 is a fine machining grade with excellent electrical properties and moisture resistance. It has low cold flow with good dimensional stability.

TYPICAL PROPERTIES

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
PHYSICAL PROPERTIES					
Specific Gravity (ASTM D792)		-			1.38
Rockwell Hardness (ASTM D785)	0.250" Build-up	M Scale	101		
Moisture Absorption (ASTM D570)	Condition A	%			
	Condition D ₁ -24/23	%	1.30		
Flexural Strength (ASTM D790)	Condition A	psi	20,000 / 15,000		
	LW / CW	(MPa)	(137.9) / (103.4)		
Flexural Modulus (ASTM D790)	Condition A	kpsi	1,300 / 1,050		
	LW / CW	(GPa)	(9.0) / (7.2)		
Tensile Strength (ASTM D638)	Condition A	psi		14,000 / 12,000	
	LW / CW	(MPa)		(96.5) / (82.7)	
Izod Impact Strength (ASTM D256)	Condition A	ft-lb/in			
	LW / CW	(J/cm)			
	Condition E-48/50	ft-lb/in			0.55 / 0.45
	LW / CW	(J/cm)			(0.29) / (0.24)
Compressive Strength (ASTM D695)	Condition A	psi			30,000
	Flatwise	(MPa)			(206.8)
Bonding Strength (ASTM D229)	Condition A	lb			1,000
		(kg)			(453.6)
Shear Strength (ASTM D732)	Condition A	psi	12,800		
	Perpendicular	(MPa)	(88.3)		



Global Thermoset Composite Solutions

TECHNICAL DATA BULLETIN

GRADE: NP630

U.L. LISTED: N

TYPICAL PROPERTIES (continued)

	UNITS	VALUE			
		Thickness Tested			
		0.0625"	0.125"	0.500"	
THERMAL PROPERTIES					
Temperature Index ¹ (UL Bulletin 746b)	Electrical / Mechanical	°C	130 / 130		
Coefficient of Thermal Expansion (IPC-TM 650-2.4.24)	X-axis / Y-axis	" / °C x10 ⁻⁶	15.0 / 19.0		
Flammability Rating (UL Bulletin 94)	Condition A	Class	HB		
ELECTRICAL PROPERTIES					
Dissipation Factor @ 1 MHz (ASTM D150)	Condition A	-			
	Condition D-24/23	-	0.050		
Relative Permittivity @ 1 MHz (ASTM D150)	Condition A	-			
	Condition D-24/23	-	6.10		
Breakdown Voltage (ASTM D149)	Condition A	kVolts	40		
	Condition D-48/50	kVolts	10		
Electric Strength (ASTM D149)	Condition A	Volts/mil (kV/cm)	700 (275.6)		
	Condition D-48/50	Volts/mil (kV/cm)	600 (236.2)		
Arc Resistance (ASTM D495)	Condition A	sec	110		
Comparative Tracking Index (ASTM D3638)		Volts	200		

¹ This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, www.norplex-micarta.com, to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.