

# NP611

## TECHNICAL DATA BULLETIN

GRADE: NP611

NEMA: XP

U.L. LISTED: N

DESCRIPTION: Hot punching general-purpose phenolic grade. Mechanical properties approach those of NP610 with improved electrical properties and moisture resistance. NP611 meets the requirements of IEC-60893-3-4-PF CP 201.

### TYPICAL PROPERTIES

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
<b>PHYSICAL PROPERTIES</b>					
<b>Specific Gravity</b> (ASTM D792)		-			1.35
<b>Rockwell Hardness</b> (ASTM D785)	0.250" Build-up	M Scale	100		
<b>Moisture Absorption</b> (ASTM D570)	Condition A	%			
	Condition D <sub>1</sub> -24/23	%	1.50		
<b>Flexural Strength</b> (ASTM D790)	Condition A	psi	29,000 / 22,000		
	LW / CW	(MPa)	(199.9) / (151.7)		
<b>Flexural Modulus</b> (ASTM D790)	Condition A	kpsi	1,200 / 900		
	LW / CW	(GPa)	(8.3) / (6.2)		
<b>Tensile Strength</b> (ASTM D638)	Condition A	psi		18,000 / 13,500	
	LW / CW	(MPa)		(124.1) / (93.1)	
<b>Izod Impact Strength</b> (ASTM D256)	Condition A	ft-lb/in			
	LW / CW	(J/cm)			
	Condition E-48/50	ft-lb/in			0.70 / 0.60
	LW / CW	(J/cm)			(0.37) / (0.32)
<b>Compressive Strength</b> (ASTM D695)	Condition A	psi			45,000
	Flatwise	(MPa)			(310.3)
<b>Bonding Strength</b> (ASTM D229)	Condition A	lb			1,100
		(kg)			(499.0)
<b>Shear Strength</b> (ASTM D732)	Condition A	psi	12,200		
	Perpendicular	(MPa)	(84.1)		

# TECHNICAL DATA BULLETIN

GRADE: NP611

NEMA: XP

U.L. LISTED: N

## TYPICAL PROPERTIES (continued)

	UNITS	VALUE		
		Thickness Tested		
		0.0625"	0.125"	0.500"
<b>THERMAL PROPERTIES</b>				
<b>Temperature Index</b> <sup>1</sup> (UL Bulletin 746b) Electrical / Mechanical	°C	130 / 130		
<b>Coefficient of Thermal Expansion</b> (IPC-TM 650-2.4.24) X-axis / Y-axis	" / °C x10 <sup>-6</sup>		13.0 / 17.0	
<b>Flammability Rating</b> Condition A (UL Bulletin 94)	Class	HB		
<b>ELECTRICAL PROPERTIES</b>				
<b>Breakdown Voltage</b> Condition A (ASTM D149)	kVolts	50		
	Condition D-48/50	kVolts	4	
<b>Electric Strength</b> Condition A (ASTM D149)	Volts/mil (kV/cm)	600 (236.2)		
<b>Arc Resistance</b> Condition A (ASTM D495)	sec		75	
<b>Comparative Tracking Index</b> (ASTM D3638)	Volts		180	

<sup>1</sup> This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

<sup>2</sup> Only applies to thicknesses greater than 0.027".

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, [www.norplex-micarta.com](http://www.norplex-micarta.com), to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.